




Appendix A


Asbestos Management Database


For Tender Purposes


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
Structure/Additions										
	Original Building	Structure	Deck	Concrete	-	Non ACM	-	-	-	-
	Original Building	Structure	Concrete	Concrete	-	Non ACM	-	-	-	-
	Original Building	Façade	Brick Veneer	Brick and Mortar	-	Non ACM	-	-	-	-
	Original Building	Not Inspected	Not Inspected	Roofing Materials	NF	Suspect ACM	VC	-	-	-
	Original Building	Windows	Interior/Exterior Frames	Silicon Sealant	-	Non ACM	-	-	-	-
	Original Building	Doors	Exterior Frames	Silicon Sealant	-	Non ACM	-	-	-	-
	Original Building	Mastic	Mastic	Floor Tile Mastic	NF	ACM	HM	32523-WOHS S68	10-Mar-08	3.5% Chrysotile
	1958 Addition	Structure	Deck	Concrete	-	Non ACM	-	-	-	-
	1958 Addition	Structure	Concrete	Concrete	-	Non ACM	-	-	-	-
	1958 Addition	Façade	Brick Veneer	Brick and Mortar	-	Non ACM	-	-	-	-
	1958 Addition	Not Inspected	Not Inspected	Roofing Materials	NF	Suspect ACM	VC	-	-	-
	1958 Addition	Windows	Interior/Exterior Frames	Silicon Sealant	-	Non ACM	-	-	-	-
	1958 Addition	Doors	Exterior Frames	Silicon Sealant	-	Non ACM	-	-	-	-
	1958 Addition	Mastic	Mastic	Floor Tile Mastic	NF	ACM	HM	32523-WOHS S28	10-Mar-08	1.9% Chrysotile
	1962 Addition	Structure	Deck	Steel	-	Non ACM	-	-	-	-
	1962 Addition	Structure	Concrete	Concrete	-	Non ACM	-	-	-	-
	1962 Addition	Façade	Brick Veneer	Brick and Mortar	-	Non ACM	-	-	-	-
	1962 Addition	Not Inspected	Not Inspected	Roofing Materials	NF	Suspect ACM	VC	-	-	-
	1962 Addition	Windows	Interior/Exterior Frames	Beige Sealant	NF	ACM	HM	S04	5-Jun-18	1% Chrysotile
	1962 Addition	Doors	Exterior Frames	Silicon Sealant	-	Non ACM	-	-	-	-
	1962 Addition	Mastic	Mastic	Floor Tile Mastic	-	Non ACM	-	32523-WOHS S15	10-Mar-08	ND
	1962 Addition	Ceiling	Ceiling Tile 1' x 1'	Brown Mastic	-	Non ACM	HM	S12	10-May-18	ND
	1966 Addition	Structure	Deck	Steel	-	Non ACM	-	-	-	-
	1966 Addition	Structure	Concrete	Concrete	-	Non ACM	-	-	-	-
	1966 Addition	Façade	Brick Veneer	Brick and Mortar	-	Non ACM	-	-	-	-
	1966 Addition	Not Inspected	Not Inspected	Roofing Materials	NF	Suspect ACM	VC	-	-	-
	1966 Addition	Windows	Interior/Exterior Frames	Beige Sealant	NF	ACM	HM	S05	5-Jun-18	5% Chrysotile
	1966 Addition	Doors	Exterior Frames	Silicon Sealant	-	Non ACM	-	-	-	-
	1966 Addition	Mastic	Mastic	Floor Tile Mastic	-	Non ACM	-	32523-WOHS S09	10-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
	1966 Addition	Ceiling	Ceiling Tile 1' x 1'	Brown Mastic	-	Non ACM	HM	S13	10-May-18	ND
	1971 Addition	Structure	Deck	Steel	-	Non ACM	-	-	-	-
	1971 Addition	Structure	Concrete	Concrete	-	Non ACM	-	-	-	-
	1971 Addition	Façade	Brick Veneer	Brick and Mortar	-	Non ACM	-	-	-	-
	1971 Addition	Not Inspected	Not Inspected	Roofing Materials	NF	Suspect ACM	VC	-	-	-
	1971 Addition	Windows	Interior/Exterior Frames	Silicon Sealant	-	Non ACM	-	-	-	-
	1971 Addition	Doors	Interior/Exterior Frames	Silicon Sealant	-	Non ACM	-	-	-	-
	1971 Addition	Mastic	Mastic	Floor Tile Mastic	NF	ACM	HM	32523-WOHS S32	10-Mar-08	3.3% Chrysotile
	1972 Addition	Structure	Deck	Steel	-	Non ACM	-	-	-	-
	1972 Addition	Structure	Concrete	Concrete	-	Non ACM	-	-	-	-
	1972 Addition	Façade	Brick Veneer	Brick and Mortar	-	Non ACM	-	-	-	-
	1972 Addition	Not Inspected	Not Inspected	Roofing Materials	NF	Suspect ACM	-	-	-	-
	1972 Addition	Windows	Interior/Exterior Frames	Beige Sealant	-	Non ACM	HM	S03	5-Jun-18	8% Chrysotile
	1972 Addition	Doors	Interior Frames	Beige Sealant	-	Non ACM	HM	S02	5-Jun-18	8% Chrysotile
	1972 Addition	Doors	Exterior Frames	Brown Sealant	-	Non ACM	HM	S01	5-Jun-18	ND
	1972 Addition	Mastic	Mastic	Floor Tile Mastic	NF	ACM	HM	32523-WOHS S88	10-Mar-08	0.75% Chrysotile
Level 1										
101	Office	Floor	Vinyl Sheet Flooring	Grey Fleck (2021)	-	Non ACM	-	-	-	-
101	Office	Wall	Concrete	-	-	Non ACM	-	-	-	-
101	Office	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
101	Office	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
102	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	SL	S07ABC	13-Mar-08	ND
102	Classroom	Wall	Wood	-	-	Non ACM	-	-	-	-
102	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
102	Classroom	Wall	Cork Board	-	-	Non ACM	-	-	-	-
102	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
102	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
102A	Lunchroom	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	SL	S07ABC	13-Mar-08	ND
102A	Lunchroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
102A	Lunchroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
102A	Lunchroom	Ceiling	Deck	Steel	-	Non ACM	-	-	-	-
102A	Lunchroom	Firespray	Firespray	Grey (2022)	-	Non ACM	-	-	-	-
102B	Head CU	Floor	Carpet	-	-	Non ACM	-	-	-	-
102B	Head CU	Wall	Concrete	-	-	Non ACM	-	-	-	-
102B	Head CU	Ceiling	Deck	Steel	-	Non ACM	-	-	-	-
102B	Head CU	Firespray	Firespray	Grey (2022)	-	Non ACM	-	-	-	-
102C	Workroom	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	SL	S07ABC	13-Mar-08	ND
102C	Workroom	Wall	Wood	-	-	Non ACM	-	-	-	-
102C	Workroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
102C	Workroom	Wall	Cork Board	-	-	Non ACM	-	-	-	-
102C	Workroom	Ceiling	Deck	Steel	-	Non ACM	-	-	-	-
102C	Workroom	Firespray	Firespray	Grey (2022)	-	Non ACM	-	-	-	-
102D	Washroom	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	SL	S07ABC	13-Mar-08	ND
102D	Washroom	Wall	Wood	-	-	Non ACM	-	-	-	-
102D	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
102D	Washroom	Wall	Cork Board	-	-	Non ACM	-	-	-	-
102D	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
103	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Grey with White	NF	ACM	HM	S18	10-Mar-08	1.8% Chrysotile
103	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
103	Classroom	Ceiling	Metal Pan	-	-	Non ACM	-	-	-	-
103	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
103A	Washroom	Floor	Vinyl Sheet Flooring	Grey Fleck (2021)	-	Non ACM	-	-	-	-
103A	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
103A	Washroom	Wall	Drywall	Post 2010	-	Non ACM	-	-	-	-
103A	Washroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
103A	Washroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
103A	Washroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
103B	Washroom	Floor	Vinyl Sheet Flooring	Grey Fleck (2021)	-	Non ACM	-	-	-	-
103B	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
103B	Washroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
103B	Washroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
103B	Washroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:								
		Original: 1955						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
103C	Workroom	Floor	Vinyl Sheet Flooring	Laminate Pattern	-	Non ACM	-	-	-	-
103C	Workroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
103C	Workroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
103C	Workroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
103C	Workroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
103C	Workroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
103D	Workroom	Floor	Vinyl Sheet Flooring	Grey Fleck (2021)	-	Non ACM	-	-	-	-
103D	Workroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
103D	Workroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
103D	Workroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
103D	Workroom	Wall	Wood	-	-	Non ACM	HM	-	13-Mar-08	ND
103D	Workroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
103D	Workroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
103E	Washroom	Floor	Vinyl Sheet Flooring	Grey Fleck (2021)	-	Non ACM	-	-	-	-
103E	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
103E	Washroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile
103E	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
103E	Washroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
103E	Washroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
104	Classroom	Floor	Vinyl Sheet Flooring	Grey Fleck (2021)	-	Non ACM	-	-	-	-
104	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
104	Classroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
104	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
104	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
104A	Greenhouse	Floor	Concrete	-	-	Non ACM	-	-	-	-
104A	Greenhouse	Walls	Glass	-	-	Non ACM	-	-	-	-
104A	Greenhouse	Ceiling	Glass	-	-	Non ACM	-	-	-	-
104A	Greenhouse	Panels	Transite Panels at Seams	Transite	NF	ACM	VC	-	-	-
104B	Greenhouse	Floor	Concrete	-	-	Non ACM	-	-	-	-
104B	Greenhouse	Wall	Concrete	-	-	Non ACM	-	-	-	-
104B	Greenhouse	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
104B	Greenhouse	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
104B	Greenhouse	Ceiling	Wood	-	-	Non ACM	-	-	-	-
104C	Storage	Floor	Vinyl Sheet Flooring	Grey Fleck (2021)	-	Non ACM	-	-	-	-
104C	Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
104C	Storage	Wall	Plywood	Wood	-	Non ACM	-	-	-	-
104C	Storage	Ceiling	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
104C	Storage	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
104C	Storage	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
104C	Storage	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
200A	Library	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	HM	S07ABC	13-Mar-08	ND
200A	Library	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
200A	Library	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2001)	-	Non ACM	-	-	-	-
200B	Library	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	HM	S07ABC	13-Mar-08	ND
200B	Library	Wall	Concrete	-	-	Non ACM	-	-	-	-
200B	Library	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
200B	Library	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2001)	-	Non ACM	-	-	-	-
200E	Library	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	HM	S07ABC	13-Mar-08	ND
200E	Library	Floor	Carpet	-	-	Non ACM	-	-	-	-
200E	Library	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
200E	Library	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
200E	Library	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2001)	-	Non ACM	-	-	-	-
200F	Library	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	HM	S07ABC	13-Mar-08	ND
200F	Library	Wall	Concrete	-	-	Non ACM	-	-	-	-
200F	Library	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
200F	Library	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND
200F	Library	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2001)	-	Non ACM	-	-	-	-
201	Office	Floor	Vinyl Floor Tile 9"x 9"	Grey with Black	NF	ACM	SL	S89	13-Mar-08	2.4% Chrysotile
201	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND
201	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
201A	Health	Floor	Vinyl Floor Tile 12"x 12"	Grey with Spots	-	Non ACM	SL	S91	10-May-18	ND
201A	Health	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	SL	S07ABC	13-Mar-08	ND
201A	Health	Wall	Concrete	-	-	Non ACM	-	-	-	-
201A	Health	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
201A	Health	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
201A	Health	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
201B	Shower	Floor	Ceramic Tile	-	-	Non ACM	-	-	-	-
201B	Shower	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
201B	Shower	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2010)	-	Non ACM	-	-	-	-
202	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Taupe	NF	ACM	SL	S84abc	13-Mar-08	2.2% Chrysotile
202	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
202	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
202	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-
202	Classroom	Ceiling	Ceiling Tile 1' x 1'	Wide Fissure Random Pinhole	-	Non ACM	SL	S83abc	13-Mar-08	NA
202A	Work Room	Floor	Vinyl Floor Tile 12"x 12"	Green	-	Non ACM	SL	S80b	13-Mar-08	ND
202A	Work Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
202A	Work Room	Ceiling	Ceiling Tile 2' x 4'	Long Fissure Random Pinhole	-	Non ACM	SL	S85abc	13-Mar-08	ND
202A	Work Room	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
202A	Work Room	Ceiling	Ceiling Tile 1' x 1'	Wide Fissure Random Pinhole	-	Non ACM	HM	S08	10-May-18	ND
202B	Office	Floor	Vinyl Floor Tile 12"x 12"	Taupe	NF	ACM	SL	S84b	13-Mar-08	2.2% Chrysotile
202B	Office	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
202B	Office	Ceiling	Ceiling Tile 2' x 4'	Random Fissure, Random Pinhole	-	Non ACM	SL	S86abc	13-Mar-08	ND
203	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Green	-	Non ACM	HM	S80	13-Mar-08	ND
203	Classroom	Wall	Plaster	-	-	Non ACM	SL	S82ce	13-Mar-08	ND
203	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-
203	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	NA
204	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Taupe	NF	ACM	HM	S84	13-Mar-08	2.2% Chrysotile
204	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
204	Classroom	Wall	Plaster	-	-	Non ACM	SL	S82b	13-Mar-08	ND
204	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
204	Classroom	Ceiling	Ceiling Tile 1' x 1'	Wide Fissure Random Pinhole	-	Non ACM	HM	S08	10-May-18	ND
205	Kitchen	Floor	Vinyl Floor Tile 12"x 12"	Green	-	Non ACM	HM	S80	13-Mar-08	ND
205	Kitchen	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
205	Kitchen	Wall	Plaster	-	-	Non ACM	SL	S82ce	13-Mar-08	ND
205	Kitchen	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-
206	Work Room	Floor	Vinyl Floor Tile 12"x 12"	Green	-	Non ACM	SL	S80b	13-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
206	Work Room	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
206	Work Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
206	Work Room	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	SL	S77b	13-Mar-08	ND
206A	Work Room	Floor	Vinyl Floor Tile 12"x 12"	Green	-	Non ACM	SL	S80b	13-Mar-08	ND
206A	Work Room	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
206A	Work Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
206A	Work Room	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	SL	S77b	13-Mar-08	ND
207	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Grey/Green	NF	ACM	SL	S88abc	13-Mar-08	2.7% Chrysotile
207	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
207	Classroom	Wall	Plaster	-	-	Non ACM	SL	S82ce	13-Mar-08	ND
207	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-
207	Classroom	Above Ceiling	Ceiling Tile 1' x 1'	Craters with Dots	-	Non ACM	SL	S87abc	13-Mar-08	ND
207	Classroom	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
207A	Office	Floor	Carpet	-	-	Non ACM	-	-	-	-
207A	Office	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
207A	Office	Ceiling	Ceiling Tile 1' x 1'	Wide Fissure Random Pinhole	-	Non ACM	SL	S08ABC	10-May-18	ND
207C	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Grey/Green	NF	ACM	SL	S88abc	13-Mar-08	2.7% Chrysotile
207C	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
207C	Classroom	Wall	Plaster	-	-	Non ACM	SL	S82ce	13-Mar-08	ND
207C	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-
207C	Classroom	Above Ceiling	Ceiling Tile 1' x 1'	Craters with Dots	-	Non ACM	SL	S87abc	13-Mar-08	ND
207C	Classroom	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
208	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Green	-	Non ACM	HM	S80	13-Mar-08	ND
208	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
208	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
208	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	NA
208	Classroom	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
210	Office	Floor	Vinyl Floor Tile 12"x 12"	Grey Oatmeal	-	Non ACM	HM	S90	13-Mar-08	ND
210	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND
210	Office	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
210	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (1997)	-	Non ACM	-	-	-	-
210	Office	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-


		School Name		Legend:					Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable					All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:							Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955									
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011									
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type	
210A	Office	Floor	Carpet	-	-	Non ACM	-	-	-	-	
210A	Office	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile	
210A	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210A	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-	
210B	Office	Floor	Carpet	-	-	Non ACM	-	-	-	-	
210B	Office	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile	
210B	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210B	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-	
210C	Office	Floor	Carpet	-	-	Non ACM	-	-	-	-	
210C	Office	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile	
210C	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210C	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-	
210D	Office	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile	
210D	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210D	Office	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	ND	
210E	Office	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile	
210E	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210E	Office	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	ND	
210F	Office	Floor	Vinyl Floor Tile 9"x 9"	Green with Faded Streak	NF	ACM	SL	S76abc	13-Mar-08	1.4% Chrysotile	
210F	Office	Wall	Concrete	-	-	Non ACM	-	-	-	-	
210F	Office	Ceiling	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210G	Office	Floor	Carpet	-	-	Non ACM	-	-	-	-	
210G	Office	Wall	Wood Panel	-	-	Non ACM	-	-	-	-	
210G	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210G	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-	
2101H	Office	Floor	Vinyl Floor Tile 9"x 9"	Taupe with Spots	NF	ACM	HM	S96abc	13-Mar-08	1.5% Chrysotile	
2101H	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
2101H	Office	Ceiling	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210I	Office	Floor	Carpet	-	-	Non ACM	-	-	-	-	
210I	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
210I	Office	Ceiling	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	
300	Mechanical	Floor	Concrete	-	-	Non ACM	-	-	-	-	


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
300	Mechanical	Wall	Concrete	-	-	Non ACM	-	-	-	-
300	Mechanical	Deck	Concrete	-	-	Non ACM	-	-	-	-
300	Mechanical	Piping	Pipe Insulation	Air Cell	F	ACM	HM	1680.894.04	11-Sep-90	>75% Amosite
300	Mechanical	Mechanical	Mechanical Insulation	Boiler Breaching	F	ACM	SL	1680.894.05	11-Sep-90	50-75% Chrysotile; 25-50% Amosite
300	Mechanical	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
300	Mechanical	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
300A	Mechanical	Floor	Concrete	-	-	Non ACM	-	-	-	-
300A	Mechanical	Wall	Concrete	-	-	Non ACM	-	-	-	-
300A	Mechanical	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
300A	Mechanical	Deck	Concrete	-	-	Non ACM	-	-	-	-
300A	Mechanical	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
300A	Mechanical	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
301	Office	Floor	Hardwood	-	-	Non ACM	-	-	-	-
301	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND
301	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (1997)	-	Non ACM	VC	-	-	-
301	Office	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	ND
301C	Office	Floor	Hardwood	-	-	Non ACM	-	-	-	-
301C	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND
301C	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (1997)	-	Non ACM	VC	-	-	-
301C	Office	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	ND
301D	Office	Floor	Hardwood	-	-	Non ACM	-	-	-	-
301D	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND
301D	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (1997)	-	Non ACM	VC	-	-	-
301D	Office	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	ND
301E	Office	Floor	Hardwood	-	-	Non ACM	-	-	-	-
301E	Office	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND
301E	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (1997)	-	Non ACM	VC	-	-	-
301E	Office	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	ND
302	Work Room	Floor	Vinyl Floor Tile 12"x 12"	Cream with Brown	NF	ACM	SL	S94abc	13-Mar-08	1.2% Chrysotile
302	Work Room	Wall	Plaster	-	-	Non ACM	SL	S82g	13-Mar-08	ND
302	Work Room	Ceiling	Ceiling Tile 2' x 2'	Random Fissure	-	Non ACM	SL	S93abc	13-Mar-08	ND
302	Work Room	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
304	Office	Floor	Vinyl Floor Tile 12"x 12"	Brown Oatmeal	NF	ACM	SL	S95abc	13-Mar-08	0.75% Chrysotile
304	Office	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
304	Office	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (2001)	-	Non ACM	VC	-	-	-
304	Office	Ducting	Duct Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
304	Office	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
305	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	SL	S07ABC	13-Mar-08	ND
305	Classroom	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
305	Classroom	Ceiling	Ceiling Tile 1' x 1'	Thick Fissure Pinhole	-	Non ACM	HM	S45	13-Mar-08	ND
305A	Office	Floor	Vinyl Sheet Flooring	Grey Dense Fleck (Post 2018)	-	Non ACM	-	-	-	-
305A	Office	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
305A	Office	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile
305A	Office	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile
305A	Office									
305A	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	-	-	-	-
305B	Storage	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile
305B	Storage	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
305B	Storage	Ceiling	Ceiling Tile 1' x 1'	Thick Fissure Pinhole	-	Non ACM	HM	S45	13-Mar-08	ND
305D	Washroom	Floor	Vinyl Sheet Flooring	Grey Dense Fleck (Post 2018)	-	Non ACM	-	-	-	-
305D	Washroom	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
305D	Washroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile
305D	Washroom	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile
305E	Kitchen	Floor	Vinyl Sheet Flooring	Grey Dense Fleck (Post 2018)	-	Non ACM	-	-	-	-
305E	Kitchen	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
305E	Kitchen	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile
305E	Kitchen	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile
305E	Kitchen	Ceiling	Ceiling Tile 2' x 2'	Thick Fissure Pinhole	-	Non ACM	HM	S06	10-May-18	ND
305F	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	SL	S07ABC	13-Mar-08	ND
305F	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile
305F	Classroom	Ceiling	Ceiling Tile 1' x 1'	Thick Fissure Pinhole	-	Non ACM	HM	S45	13-Mar-08	ND
305G	Office	Floor	Vinyl Floor Tile 12"x 12"	Brown Oatmeal	NF	ACM	HM	S95	13-Mar-08	0.75% Chrysotile
305G	Office	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
305G	Office	Ceiling	Ceiling Tile 1' x 1'	Craters with Dots	-	Non ACM	SL	S87ac	13-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
306	Classroom	Floor	Vinyl Floor Tile 12"x 12"	White with Black Fleck	-	Non ACM	SL	S42abc	13-Mar-08	ND
306	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
306	Classroom	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (1997)	-	Non ACM	-	-	-	-
306	Classroom	Wall	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-
306	Classroom	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
307	Classroom	Floor	Vinyl Floor Tile 12"x 12"	White with Black Fleck	-	Non ACM	HM	S42	13-Mar-08	ND
307	Classroom	Wall	Plaster	-	-	Non ACM	SL	S43	13-Mar-08	ND
307	Classroom	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (1997)	-	Non ACM	-	-	-	-
307	Classroom	Wall	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-
307	Classroom	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
308A	Office	Floor	Hardwood	-	-	Non ACM	-	-	-	-
308A	Office	Wall	Drywall	-	-	Non ACM	-	-	-	-
308A	Office	Ceiling	Ceiling Tile 2'x2'	Dense Fissure Small Pinhole	-	Non ACM	HM	S29	13-Mar-08	ND
308	Office	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile
308	Office	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
308	Office	Ceiling	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-
308	Office	Ceiling	Ceiling Tile 2' x 2'	Dense Fissure Small Pinhole	-	Non ACM	HM	S29	13-Mar-08	ND
308	Office	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
309	Dressing Room	Floor	Vinyl Floor Tile 12"x 12"	Green with Black, White, & Grey Fleck	NF	ACM	SL	S34abc	13-Mar-08	2.2% Chrysotile
309	Dressing Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
309	Dressing Room	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
309	Dressing Room	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
309A	Washroom	Floor	Vinyl Floor Tile 12"x 12"	Green with Black, White, & Grey Fleck	NF	ACM	SL	S34abc	13-Mar-08	2.2% Chrysotile
309A	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
309A	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
310	No Access	Not Inspected								
310A	No Access	Not Inspected								
311	Washroom	Floor	Vinyl Floor Tile 12"x 12"	Grey Dense Fleck (Post 2018)	-	Non ACM	-	-	-	-
311	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
311	Washroom	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
311	Washroom	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
312	Washroom	Floor	Vinyl Floor Tile 12"x 12"	Grey with Brown & White Fleck	-	Non ACM	SL	S37abc	13-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
312	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
312	Washroom	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
312	Washroom	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
313	Storage	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile
313	Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
313	Storage	Ceiling	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
314	Storage	Floor	Vinyl Floor Tile 12"x 12"	Beige Dense Fleck (Post 2010)	-	Non ACM	-	-	-	-
314	Storage	Floor	Concrete	-	-	Non ACM	-	-	-	-
314	Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
314	Storage	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
314	Storage	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2010)	-	Non ACM	-	-	-	-
314	Storage	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
315	Storage to Washroom	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile
315	Storage to Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
315	Storage to Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
315A	Washroom	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile
315A	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
315A	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
315A	Washroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
316	Office	Floor	Vinyl Floor Tile 12"x 12"	Grey with Brown & White Fleck	-	Non ACM	HM	S37	13-Mar-08	ND
316	Office	Wall	Concrete	-	-	Non ACM	-	-	-	-
316	Office	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
317	Kitchen/Dishwasher	Floor	Vinyl Floor Tile 12"x 12"	Grey with Brown & White Fleck	-	Non ACM	HM	S37	13-Mar-08	ND
317	Kitchen/Dishwasher	Wall	Concrete	-	-	Non ACM	-	-	-	-
317	Kitchen/Dishwasher	Ceiling	Ceiling Tile 2' x 2'	Solid Pattern	-	Non ACM	SL	S38abc	13-Mar-08	ND
317	Kitchen/Dishwasher	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (1994)	-	Non ACM	-	-	-	-
317	Kitchen/Dishwasher	Above Ceiling	Texture Coat	-	F	ACM	HM	S39	13-Mar-08	20% Chrysotile
318	Staff Dining	Floor	Vinyl Sheet Flooring	Grey Cloudy (Post 2018)	-	Non ACM	-	-	-	-
318	Staff Dining	Wall	Concrete	-	-	Non ACM	-	-	-	-
318	Staff Dining	Ceiling	Plaster	-	-	Non ACM	SL	S41abc	13-Mar-08	ND
318	Staff Dining	Above Ceiling	Texture Coat	-	F	ACM	HM	S39	13-Mar-08	20% Chrysotile
318	Staff Dining	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
319	Servery	Floor	Vinyl Floor Tile 12"x 12"	Grey with Brown & White Fleck	-	Non ACM	HM	S37	13-Mar-08	ND
319	Servery	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
319	Servery	Ceiling	Ceiling Tile 2' x 2'	Solid Pattern	-	Non ACM	SL	S38abc	13-Mar-08	ND
319	Servery	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (1994)	-	Non ACM	-	-	-	-
319	Servery	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
320	Servery	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
320	Servery	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
320	Servery	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
321	Custodial Room	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
321	Custodial Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
321	Custodial Room	Ceiling	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
323	Cafetorium	Floor	Vinyl Floor Tile 12"x 12"	Black with Specks (Post 2010)	-	Non ACM	-	-	-	-
323	Cafetorium	Floor	Vinyl Floor Tile 12"x 12"	Beige with Specks (Post 2010)	-	Non ACM	-	-	-	-
323	Cafetorium	Floor	Vinyl Floor Tile 12"x 12"	Grey with Specks (Post 2010)	-	Non ACM	-	-	-	-
323	Cafetorium	Floor	Vinyl Floor Tile 12"x 12"	Green with Specks (Post 2010)	-	Non ACM	-	-	-	-
323	Cafetorium	Wall	Concrete	-	-	Non ACM	-	-	-	-
323	Cafetorium	Ceiling	Ceiling Tile 2' x 2'	Dense Fissure Small Pinhole	-	Non ACM	SL	S29abc	13-Mar-08	ND
323	Cafetorium	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
323A	Stage	Floor	Wood	-	-	Non ACM	-	-	-	-
323A	Stage	Wall	Concrete	-	-	Non ACM	-	-	-	-
323A	Stage	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
323A	Stage	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
323A	Stage	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
323B	Stage	Floor	Concrete	-	-	Non ACM	-	-	-	-
323B	Stage	Wall	Concrete	-	-	Non ACM	-	-	-	-
323B	Stage	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
323B	Stage	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
323B	Stage	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
400A	Washroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
400A	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
400A	Washroom	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
400A	Washroom	Ceiling	Ceiling Tile 2' x 4'	Thick Fissure	-	Non ACM	SL	S65abc	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
400B	Office	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
400B	Office	Wall	Concrete	-	-	Non ACM	-	-	-	-
400B	Office	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
400B	Office	Ceiling	Ceiling Tile 2' x 4'	Textured Pinhole	-	Non ACM	SL	S10abc	10-May-18	ND
400B	Office	Ceiling	Ceiling Tile 1' x 1'	Large and Small	-	Non ACM	HM	S10	10-Mar-08	ND
400B	Office	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
400D	Storage	Floor	Concrete	-	-	Non ACM	-	-	-	-
400D	Storage	Wall	Plaster	-	-	Non ACM	HM	S64	10-Mar-08	ND
400D	Storage	Ceiling	Plaster	-	-	Non ACM	HM	S64	10-Mar-08	ND
401	Gymnasium	Floor	Wood	-	-	Non ACM	-	-	-	-
401	Gymnasium	Wall	Concrete	-	-	Non ACM	-	-	-	-
401	Gymnasium	Ceiling	Metal Pan	-	-	Non ACM	-	-	-	-
401	Gymnasium	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
401A	Storage	Floor	Vinyl Floor Tile 12"x 12"	Grey Dense Fleck (Post 2010)	-	Non ACM	-	-	-	-
401A	Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
401A	Storage	Wall	Brick	-	-	Non ACM	-	-	-	-
401A	Storage	Ceiling	Wood	-	-	Non ACM	-	-	-	-
401A	Storage	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
401B	Office	Floor	Vinyl Floor Tile 12"x 12"	Grey Dense Fleck (Post 2010)	-	Non ACM	-	-	-	-
401B	Office	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
401B	Office	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
401C	Washroom	Floor	Vinyl Floor Tile 12"x 12"	Grey Dense Fleck (Post 2010)	-	Non ACM	-	-	-	-
401C	Washroom	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
401C	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
401C	Washroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
401D	Football Storage Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
401D	Football Storage Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
401D	Football Storage Room	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
401D	Football Storage Room	Piping	Pipe Fitting	Fiberglass/PVC	-	Non ACM	-	-	-	-
402	Gymnasium	Floor	Wood	-	-	Non ACM	-	-	-	-
402	Gymnasium	Wall	Concrete	-	-	Non ACM	-	-	-	-
402	Gymnasium	Ceiling	Metal Pan	-	-	Non ACM	-	-	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
402	Gymnasium	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
402A	Weight Room	Floor	Rubber	-	-	Non ACM	-	-	-	-
402A	Weight Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
402A	Weight Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
402A	Weight Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
402A	Weight Room	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
402B	Gym Storage	Floor	Vinyl Floor Tile 12"x 12"	Blue with Blue and White Fleck	NF	ACM		-	-	-
402B	Gym Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
402B	Gym Storage	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
402A	Gym Storage	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
402A	Gym Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
402A	Gym Storage	Wall	Plaster	-	-	Non ACM	SL	S64abc	10-Mar-08	ND
402A	Gym Storage	Wall	Plaster	-	-	Non ACM	HM	S64	10-Mar-08	ND
402B	Gym Storage	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
402B	Gym Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
402B	Gym Storage	Wall	Plaster	-	-	Non ACM	SL	S64abc	10-Mar-08	ND
402B	Gym Storage	Wall	Plaster	-	-	Non ACM	HM	S64	10-Mar-08	ND
402C	Gym Storage	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
402C	Gym Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
402C	Gym Storage	Wall	Plaster	-	-	Non ACM	SL	S64abc	10-Mar-08	ND
402C	Gym Storage	Wall	Plaster	-	-	Non ACM	HM	S64	10-Mar-08	ND
402C	Electrical Room	Not Inspected								
403	Gym	Floor	Hardwood	-	-	Non ACM	-	-	-	-
403	Gym	Wall	Concrete	-	-	Non ACM	-	-	-	-
403	Gym	Deck	Metal Pan	Steel	-	Non ACM	-	-	-	-
403	Gym	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
403A	Storage	Floor	Concrete	-	-	Non ACM	-	-	-	-
403A	Storage	Wall	Plaster	-	-	Non ACM	SL	S64abc	10-Mar-08	ND
403A	Storage	Wall	Plaster	-	-	Non ACM	HM	S64	10-Mar-08	ND
403B	Changeroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
403B	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
403B	Changeroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small	-	Non ACM	HM	S10	10-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
403B	Changeroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Small Pinhole	-	Non ACM	SL	S01ABC	10-May-18	ND
403B	Changeroom	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
403C	Changeroom	Floor	Ceramic Tile	-	-	Non ACM	-	-	-	-
403C	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
403C	Changeroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small	-	Non ACM	HM	S10	10-Mar-08	ND
403C	Changeroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Small Pinhole	-	Non ACM	SL	S01ABC	10-May-18	ND
403C	Changeroom	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
403D	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
403D	Changeroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small	-	Non ACM	HM	S10	10-Mar-08	ND
403D	Changeroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Small Pinhole	-	Non ACM	SL	S01ABC	10-May-18	ND
403D	Changeroom	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
403E	Changeroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
403E	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
403E	Changeroom	Ceiling	Ceramic Tile	-	-	Non ACM	-	-	-	-
403E	Changeroom	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
403F	Changeroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
403F	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
403F	Changeroom	Ceiling	Ceramic Tile	-	-	Non ACM	-	-	-	-
403F	Changeroom	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
403G	Changeroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
403G	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
403G	Changeroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small	-	Non ACM	HM	S10	10-Mar-08	ND
403G	Changeroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Small Pinhole	-	Non ACM	HM	S01	10-May-18	ND
403G	Changeroom	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
404	Music	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	SL	S26abc	13-Mar-08	0.75% Chrysotile
404	Music	Floor	Vinyl Floor Tile 12"x 12"	Teal Dense Fleck	-	Non ACM	SL	S07	13-Mar-08	ND
404	Music	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
404	Music	Wall	Concrete	-	-	Non ACM	-	-	-	-
404	Music	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2020)	-	Non ACM	-	-	-	-
404	Music	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite
404	Music	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
404A	Practice Room	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	HM	S26	13-Mar-08	0.75% Chrysotile


		School Name		Legend:					Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable					All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:							Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955									
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011									
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type	
404A	Practice Room	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND	
404A	Practice Room	Wall	Concrete	-	-	Non ACM	-	-	-	-	
404A	Practice Room	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite	
404B	Practice Room	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	HM	S26	13-Mar-08	0.75% Chrysotile	
404B	Practice Room	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND	
404B	Practice Room	Wall	Concrete	-	-	Non ACM	-	-	-	-	
404B	Practice Room	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite	
404C	Practice Room	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	HM	S26	13-Mar-08	0.75% Chrysotile	
404C	Practice Room	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND	
404C	Practice Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2020)	-	Non ACM	-	-	-	-	
404C	Practice Room	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite	
404D	Practice Room	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	HM	S26	13-Mar-08	0.75% Chrysotile	
404D	Practice Room	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND	
404D	Practice Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2020)	-	Non ACM	-	-	-	-	
404D	Practice Room	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite	
404E	Practice Room	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	HM	S26	13-Mar-08	0.75% Chrysotile	
404E	Practice Room	Floor	Concrete	-	-	Non ACM	-	-	-	-	
404E	Practice Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile	
404E	Practice Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2020)	-	Non ACM	-	-	-	-	
404E	Practice Room	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite	
404F	Practice Room	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	HM	S26	13-Mar-08	0.75% Chrysotile	
404F	Practice Room	Floor	Concrete	-	-	Non ACM	-	-	-	-	
404F	Practice Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile	
404F	Practice Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2020)	-	Non ACM	-	-	-	-	
404F	Practice Room	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite	
405	Classroom	Floor	Carpet	-	-	Non ACM	-	-	-	-	
405	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Beige with Grey Fleck	-	Non ACM	SL	S25abc	13-Mar-08	Trace Chrysotile	
405	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24	13-Mar-08	ND	
405	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
405	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2020)	-	Non ACM	-	-	-	-	
405	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite	
405	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
405A	Workroom	Floor	Vinyl Floor Tile 9"x 9"	Beige with Grey Fleck	-	Non ACM	SL	S25abc	13-Mar-08	Trace Chrysotile
405A	Workroom	Floor	Floor Tile Mastic	Black Mastic	-	-	HM	S26	13-Mar-08	Non Detect
405A	Workroom	Floor	Concrete	-	-	-	-	-	-	-
405A	Workroom	Wall	Plaster	-	-	Non ACM	HM	S24	13-Mar-08	ND
405A	Workroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2020)	-	-	-	-	-	-
405A	Workroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite
409	Changeroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
409	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
409	Changeroom	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
409	Changeroom	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
409A	Changeroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
409A	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
409A	Changeroom	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
409A	Changeroom	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
409B	Washroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
409B	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
409B	Washroom	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
409B	Washroom	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
410	Washroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
410	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
410	Washroom	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
410	Washroom	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
410A	Changeroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
410A	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
410A	Changeroom	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
410A	Changeroom	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
410B	Changeroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
410B	Changeroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
410B	Changeroom	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-
410B	Changeroom	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
410C	Tuck Shop	Floor	Vinyl Floor Tile 9"x 9"	Grey with White Streaks	NF	ACM	SL	S68abc	10-Mar-08	1.3% Chrysotile
410C	Tuck Shop	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
410C	Tuck Shop	Ceiling	Ceiling Tile 1' x 1'	Large and Small	-	Non ACM	HM	S77	10-Mar-08	ND
500	Washroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
500	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
500	Washroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
500	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
500	Washroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
500	Pipe Chase	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
500	Pipe Chase	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
500	Pipe Chase	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
500A	Washroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
500A	Washroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
500A	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
500A	Washroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
500A	Washroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
501	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Tan with Red and Black	NF	ACM	SL	S28abc	13-Mar-08	4.1% Chrysotile
501	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
501	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
501	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	VC	-	-	-
501	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
502	Workroom	Floor	Vinyl Floor Tile 12"x 12"	White with Brown (Post 2010)	-	Non ACM	-	-	-	-
502	Workroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
502	Workroom	Wall	Drywall	Post 2010	-	Non ACM	-	-	-	-
502	Workroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
502	Workroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	-	-	-	-
503	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Tan with Red and Black	NF	ACM	HM	S28	13-Mar-08	4.1% Chrysotile
503	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
503	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
503	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	VC	-	-	-
503	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
504	Workroom	Floor	Vinyl Floor Tile 12"x 12"	White with Brown (Post 2010)	-	Non ACM	-	-	-	-
504	Workroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
504	Workroom	Wall	Drywall	Post 2010	-	Non ACM	-	-	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
504	Workroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
504	Workroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	-	-	-	-
504A	Storage	Floor	Vinyl Floor Tile 12"x 12"	White with Brown (Post 2010)	-	Non ACM	-	-	-	-
504A	Storage	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
504A	Storage	Wall	Wood	-	-	Non ACM	-	-	-	-
504A	Storage	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
504B	Workroom	Floor	Vinyl Floor Tile 12"x 12"	White with Brown (Post 2010)	-	Non ACM	-	-	-	-
504B	Workroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
504B	Workroom	Wall	Drywall	Post 2010	-	Non ACM	-	-	-	-
504B	Workroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
504B	Workroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	-	-	-	-
505	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Green with White Streaks	NF	ACM	HM	S21	13-Mar-08	0.5% Chrysotile
505	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
505	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
505	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	-	-	-	-
505	Classroom	Deck	Metal Pan	Steel	-	Non ACM	-	-	-	-
505	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
506	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Blue with White Streaks	-	Non ACM	SL	S20abc	10-Mar-08	0.5% Chrysotile
506	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	-
506	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
507	Classroom	Floor	Vinyl Sheet Flooring	Blue Dense Fleck (Post 2018)	-	Non ACM	-	-	-	-
507	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	-
507	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
508	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Brown Oatmeal (Post 2010)	-	Non ACM	-	-	-	-
508	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	-
508	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
508	Classroom	Ceiling	Ceiling Tile 1' x 1'	Pattern/Date	-	Non ACM	-	-	-	-
508	Classroom	Wall	Metal Partition	-	-	Non ACM	-	-	-	-
509	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Brown Oatmeal (Post 2010)	-	Non ACM	-	-	-	-
509	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
509	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
509A	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Brown Oatmeal (Post 2010)	-	Non ACM	-	-	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
509A	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
509A	Classroom	Wall	Drywall	Drywall Joint Compound (Post 2000)	-	Non ACM	-	-	-	-
509A	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
509B	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Brown Oatmeal (Post 2010)	-	Non ACM	-	-	-	-
509B	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
509B	Classroom	Wall	Drywall	Drywall Joint Compound (Post 2010)	-	Non ACM	-	-	-	-
509B	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
510	Classroom	Floor	Concrete	-	-	Non ACM	-	-	-	-
510	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
510	Classroom	Wall	Plaster	-	-	Non ACM	SL	S03BC	10-May-18	ND
510	Classroom	Wall	Metal Partition	-	-	Non ACM	-	-	-	-
510	Classroom	Ceiling	Ceiling Tie	Fibreglass	-	Non ACM	-	-	-	-
510	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
510	Classroom	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
510A	Classroom	Floor	Concrete	-	-	Non ACM	-	-	-	-
510A	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
510A	Classroom	Wall	Metal Partition	-	-	Non ACM	-	-	-	-
510A	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
510A	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
511	Storage Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
511	Storage Room	Wall	Plaster	-	-	Non ACM	HM	S02, S05, S19	10-Mar-08	ND
511	Storage Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
511	Storage Room	Ceiling	Plaster	-	-	Non ACM	HM	S02, S05, S19	10-Mar-08	ND
511A	Cyclone Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
511A	Cyclone Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
511A	Cyclone Room	Ceiling	Metal Pan	Open Web Steel Joists	-	Non ACM	-	-	-	-
511B	Cyclone Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
511B	Cyclone Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
511B	Cyclone Room	Ceiling	Metal Pan	Open Web Steel Joists	-	Non ACM	-	-	-	-
511B	Cyclone Room	Mechanical	Cyclone	-	-	Non ACM	-	-	-	-
511C	Fan Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
511C	Fan Room	Wall	Concrete	-	-	Non ACM	-	-	-	-


		School Name		Legend:					Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable					All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:							Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955									
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011									
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type	
511C	Fan Room	Wall	Brick	-	-	Non ACM	-	-	-	-	
511C	Fan Room	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile	
511C	Fan Room	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-	
511D	Stairwell	Floor	Vinyl Floor Tile 12"x 12"	Brown Oatmeal (Post 2010)	-	Non ACM	-	-	-	-	
511D	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-	
511D	Stairwell	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-	
511D	Stairwell	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
511E	Stairwell	Floor	Vinyl Floor Tile 12"x 12"	Brown Oatmeal (Post 2010)	-	Non ACM	-	-	-	-	
511E	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-	
511E	Stairwell	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-	
512	Classroom	Floor	Wood	-	-	Non ACM	-	-	-	-	
512	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Grey with White	NF	ACM	SL	S18abc	10-Mar-08	1.8% Chrysotile	
512	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
512	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
512	Classroom	Ceiling	Ceiling Tile 2' x 4'	Long Fissure Random Pinhole	-	Non ACM	-	-	-	-	
512	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
512B	Small Storage	Floor	Wood	-	-	Non ACM	-	-	-	-	
512B	Small Storage	Wall	Plaster	-	-	Non ACM	SL	S03A	10-May-18	ND	
512B	Small Storage	Ceiling	Ceiling Tile 1' x 1'	Cellulose	-	Non ACM	-	-	-	-	
512C	Large Storage	Floor	Wood	-	-	Non ACM	-	-	-	-	
512C	Large Storage	Wall	Plaster	-	-	Non ACM	HM	S03	10-May-18	ND	
512C	Large Storage	Ceiling	Ceiling Tile 1' x 1'	Large Pinhole	-	Non ACM	HM	S10	10-May-18	ND	
513	Media Room	Floor	Carpet	-	-	Non ACM	-	-	-	-	
513	Media Room	Wall	Concrete	-	-	Non ACM	-	-	-	-	
513	Media Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile	
513	Media Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
513	Media Room	Piping	Pipe Fitting	Fiberglass/PVC	-	Non ACM	-	-	-	-	
513A	Staff Room	Floor	Vinyl Floor Tile 12"x 12"	Tan with Brown	NF	ACM	SL	S15abc	10-Mar-08	3.6% Chrysotile	
513A	Staff Room	Wall	Concrete	-	-	Non ACM	-	-	-	-	
513A	Staff Room	Wall	Wood Panel	-	-	Non ACM	-	-	-	-	
513A	Staff Room	Ceiling	Ceiling Tile 2' x 4'	Medium Fissure Random Pinhole	-	Non ACM	HM	S02ABC	10-May-18	ND	
513A	Staff Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
513B	Staff Room	Floor	Vinyl Floor Tile 12"x 12"	Brown Dense Fleck (Post 2010)	-	Non ACM	-	-	-	-
513B	Staff Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
513B	Staff Room	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04, S77	13-Mar-08	ND
513B	Staff Room	Piping	Pipe Insulation	Horsehair	-	Non ACM	-	-	-	-
513B	Staff Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
513C	Closet	Floor	Vinyl Floor Tile 12"x 12"	White with Grey Fleck (Post 2010)	-	Non ACM	-	-	-	-
513C	Closet	Wall	Concrete	-	-	Non ACM	-	-	-	-
513C	Closet	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
513C	Closet	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
513E	Storage Room	Floor	Vinyl Floor Tile 12"x 12"	White with Grey Fleck (Post 2010)	-	Non ACM	-	-	-	-
513E	Storage Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
513E	Storage Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
513E	Storage Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
514	Classroom	Floor	Wood	-	-	Non ACM	-	-	-	-
514	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
514	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
514	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissures and Pinholes	-	Non ACM	SL	S13abc	10-Mar-08	ND
514	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
514A	Classroom	Floor	Carpet	-	-	Non ACM	-	-	-	-
514A	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
514A	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
514A	Classroom	Wall	Ceiling Tile 1' x 1'	Acoustic Tiles	-	Non ACM	SL	S14abc	10-Mar-08	ND
514A	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
514A	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
514B	Storage Room	Floor	Carpet	-	-	Non ACM	-	-	-	-
514B	Storage Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
514B	Storage Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
514B	Storage Room	Wall	Ceiling Tile 1' x 1'	Acoustic Tiles	-	Non ACM	HM	S14abc	10-Mar-08	ND
514B	Storage Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
514E	Closet	Floor	Concrete	-	-	Non ACM	-	-	-	-
514E	Closet	Wall	Drywall	Post 2010	-	Non ACM	-	-	-	-
514E	Closet	Ceiling	Metal Pan	Open Web Steel Joists	-	Non ACM	-	-	-	-


		School Name		Legend:					Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable					All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:							Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955									
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011									
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type	
515	Classroom	Floor	Concrete	-	-	Non ACM	-	-	-	-	
515	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND	
515	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
515	Classroom	Ceiling	Metal Pan	Open Web Steel Joists	-	Non ACM	-	-	-	-	
515A	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Brown with White Flecks	NF	ACM	HM	S09abc	10-Mar-08	1.3% Chrysotile	
515A	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND	
515A	Classroom	Ceiling	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND	
515B	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Brown with White Flecks	NF	ACM	SL	S09abc	10-Mar-08	1.3% Chrysotile	
515B	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND	
515B	Classroom	Ceiling	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND	
515B	Classroom	Floor	Concrete	-	-	Non ACM	-	-	-	-	
515B	Classroom	Wall	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND	
515B	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
515B	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large Pinhole	-	Non ACM	SL	S10abc	-	ND	
515B	Classroom	Ceiling	Ceiling Tile 1' x 1'	Long Fissure Small Pinhole	-	Non ACM	SL	S11abc	-	ND	
515B	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
516	Classroom	Floor	Wood	-	-	Non ACM	-	-	-	-	
516	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	SL	S26abc	13-Mar-08	0.75% Chrysotile	
516	Classroom	Wall	Drywall	Drywall Joint Compound	NF	ACM	SL	S07abc	10-Mar-08	1.8% Chrysotile	
516	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
516	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	SL	S12abc	10-Mar-08	2.1% Amosite	
516	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
516	Classroom	Piping	Pipe Insulation	Horsehair	-	Non ACM	-	-	-	-	
516A	Small Store Room	Floor	Wood	-	-	Non ACM	-	-	-	-	
516A	Small Store Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile	
516A	Small Store Room	Ceiling	Ceiling Tile 2' x 2'	Large Pinhole (Drywall)	-	Non ACM	-	-	-	-	
516A	Small Store Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
516B	Large Store Room	Floor	Wood	-	-	Non ACM	-	-	-	-	
516B	Large Store Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S07	10-Mar-08	1.8% Chrysotile	
516B	Large Store Room	Wall	Concrete	-	-	Non ACM	-	-	-	-	
516B	Large Store Room	Ceiling	Ceiling Tile 2' x 2'	Large Pinhole (Drywall)	-	Non ACM	-	-	-	-	
516C	Store Room	Floor	Wood	-	-	Non ACM	-	-	-	-	


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
516C	Store Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	SL	S07abc	10-Mar-08	1.8% Chrysotile
516C	Store Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
516C	Store Room	Ceiling	Ceiling Tile 2' x 2'	Large Pinhole (Drywall)	-	Non ACM	-	-	-	-
517	Classroom	Floor	Concrete	-	-	Non ACM	-	-	-	-
517	Classroom	Floor	Wood	-	-	Non ACM	-	-	-	-
517	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
517	Classroom	Wall	Brick	-	-	Non ACM	-	-	-	-
517	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 2010)	-	Non ACM	-	-	-	-
517	Classroom	Piping	Pipe Fitting	Fiberglass/PVC	-	Non ACM	-	-	-	-
517	Classroom	Piping	Pipe Fitting	Cellulose	-	Non ACM	-	-	-	-
517A	Classroom	Floor	Concrete	-	-	Non ACM	-	-	-	-
517A	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
517A	Classroom	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
518	Classroom	Floor	Concrete	-	-	Non ACM	-	-	-	-
518	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
518	Classroom	Wall	Drywall	Drywall Joint Compound	-	Non ACM	SL	S01abc	10-Mar-08	ND
518	Classroom	Wall	Brick	-	-	Non ACM	-	-	-	-
518	Classroom	Ceiling	Ceiling Tile 2' x 4'	Long Fissure Random Pinhole	NF	ACM	SL	S03abc	10-Mar-08	1.7% Amosite, 0.6% Chrysotile
518	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
518A	Instrument Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
518A	Instrument Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
518A	Instrument Room	Ceiling	Ceiling Tile 2' x 4'	Long Fissure Random Pinhole	NF	ACM	SL	S03abc	10-Mar-08	1.7% Amosite, 0.6% Chrysotile
518A	Instrument Room	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
518B	Storage Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
518B	Storage Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
518B	Storage Room	Ceiling	Ceiling Tile 2' x 4'	Long Fissure Random Pinhole	NF	ACM	SL	S03abc	10-Mar-08	1.7% Amosite, 0.6% Chrysotile
518B	Storage Room	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
518B	Storage Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
518B	Storage Room	Piping	Pipe Insulation	Air Cell	F	ACM	HM	1680.894.04	11-Sep-90	>75% Amosite
518C	Fan Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
518C	Fan Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
518C	Fan Room	Ceiling	Concrete	-	-	Non ACM	-	-	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
518C	Fan Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
518C	Fan Room	Piping	Pipe Insulation	Air Cell	F	ACM	HM	1680.894.04	11-Sep-90	>75% Amosite
518C	Fan Room	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
801	Corridor - 1966	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
801	Corridor - 1966	Wall	Plaster	-	-	Non ACM	SL	S72abc	13-Mar-08	ND
801	Corridor - 1966	Ceiling	Ceiling Tile 2' x 2'	Large and Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
801	Corridor - 1966	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
801	Corridor - 1966	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
801	Corridor - 1966	Piping	Pipe Fitting	Parged Cement	F	ACM	SL	1680.894.03	11-Sep-90	50-75% Chrysotile
801	Corridor - 1966	Firespray	Firespray	Spray-applied	F	ACM	SL	S71abc	13-Mar-08	3.8% Chrysotile
802	Corridor - 1955	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
802	Corridor - 1955	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND
802	Corridor - 1955	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (1991)	-	Non ACM	-	-	-	-
802	Corridor - 1955	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
802	Corridor - 1955	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	13-Mar-08	ND
802	Corridor - 1955	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
802	Corridor - 1955	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
802	Corridor - 1955	Piping	Pipe Insulation	Air Cell	F	ACM	HM	1680.894.04	11-Sep-90	>75% Amosite
803	Corridor - 1955	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
803	Corridor - 1955	Wall	Plaster	-	-	Non ACM	SL	S82b	13-Mar-08	ND
803	Corridor - 1955	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole	-	Non ACM	SL	S92abc	13-Mar-08	ND
803	Corridor - 1955	Piping	Pipe Insulation	Air Cell	F	ACM	HM	1680.894.04	11-Sep-90	>75% Amosite
803	Corridor - 1955	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
804	Corridor - 1955	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
804	Corridor - 1955	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
804	Corridor - 1955	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-
804	Corridor - 1955	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
804A	Corridor - 1955	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
804A	Corridor - 1955	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
804A	Corridor - 1955	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2004)	-	Non ACM	-	-	-	-
805	Corridor - 1955	Floor	Vinyl Floor Tile 12"x 12"	Grey with Brown & White Fleck	-	Non ACM	HM	S37	13-Mar-08	ND
805	Corridor - 1955	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
805	Corridor - 1955	Ceiling	Ceiling Tile 2' x 2'	Dense Fissure Small Pinhole	-	Non ACM	HM	S29	13-Mar-08	ND
805	Corridor - 1955	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
807	Corridor - 1971	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
807	Corridor - 1971	Wall	Plaster	-	-	Non ACM	SL	S35e	13-Mar-08	ND
807	Corridor - 1971	Ceiling	Ceiling Tile 2' x 2'	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
807	Corridor - 1971	Ceiling	Ceiling Tile 2' x 2'	Dense Fissure Small Pinhole	-	Non ACM	SL	S29abc	13-Mar-08	ND
807	Corridor - 1971	Ducting	Duct Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
807	Corridor - 1971	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
807A	Corridor	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile
807A	Corridor	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
807A	Corridor	Ceiling	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-
807A	Corridor	Ceiling	Ceiling Tile 2' x 2'	Dense Fissure Small Pinhole	-	Non ACM	HM	S29	13-Mar-08	ND
807A	Corridor	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
807B	Stage Entrance/Hallway	Floor	Vinyl Floor Tile 9"x 9"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile
807B	Stage Entrance/Hallway	Wall	Concrete	-	-	Non ACM	-	-	-	-
807B	Stage Entrance/Hallway	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
807B	Stage Entrance/Hallway	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
807C	Stage Entrance/Hallway	Floor	Vinyl Floor Tile 9"x 9"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile
807C	Stage Entrance/Hallway	Wall	Concrete	-	-	Non ACM	-	-	-	-
807C	Stage Entrance/Hallway	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
807C	Stage Entrance/Hallway	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
808	Corridor - 1955	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
808	Corridor - 1955	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
808	Corridor - 1955	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
808	Corridor - 1955	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
809	Corridor - 1962	Floor	Vinyl Floor Tile 12"x 12"	Green with Grey and White	-	Non ACM	SL	S67abc	-	-
809	Corridor - 1962	Floor	Vinyl Floor Tile 12"x 12"	Black with Grey and White	-	Non ACM	SL	S66abc	-	-
809	Corridor - 1962	Floor	Vinyl Floor Tile 12"x 12"	Brown with Brown and White Fleck	-	Non ACM	HM	S53	13-Mar-08	ND
809	Corridor - 1962	Wall	Plaster	-	-	Non ACM	SL	S64de	10-Mar-08	ND
809	Corridor - 1962	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (Post 2021)	-	Non ACM	-	-	-	-
809	Corridor - 1962	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
810	Corridor - 1958	Floor	Terrazzo	-	-	Non ACM	-	-	-	-


		School Name		Legend:					Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable					All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:							Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955									
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011									
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type	
810	Corridor - 1958	Wall	Plaster	-	-	Non ACM	SL	S27abcd	13-Mar-08	ND	
810	Corridor - 1958	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-	
810	Corridor - 1958	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	-	-	-	-	
810	Corridor - 1958	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-	
810	Corridor - 1958	Firespray	Firespray	Troweled-applied	F	ACM	HM	S23	13-Mar-08	3.2% Chrysotile	
811	Corridor - 1966	Floor	Terrazzo	-	-	Non ACM	-	-	-	-	
811	Corridor - 1966	Floor	Concrete	-	-	Non ACM	-	-	-	-	
811	Corridor - 1966	Wall	Plaster	-	-	Non ACM	SL	S24e	13-Mar-08	ND	
811	Corridor - 1966	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-	
811	Corridor - 1966	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	-	-	-	-	
811	Corridor - 1966	Firespray	Firespray	Troweled-applied	F	ACM	HM	S23	13-Mar-08	3.2% Chrysotile	
812	Corridor - 1962	Floor	Terrazzo	-	-	Non ACM	-	-	-	-	
812	Corridor - 1962	Wall	Plaster	-	-	Non ACM	HM	S24	13-Mar-08	ND	
812	Corridor - 1962	Ceiling	Ceiling Tile 2 x 2	Large & Small Pinhole	NF	ACM		-	-	-	
812	Corridor - 1962	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	-	-	-	-	
812	Corridor - 1962	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
812	Corridor - 1962	Firespray	Firespray	-	F	ACM	HM	S23	13-Mar-08	3.2% Chrysotile	
813	Corridor - 1972	Floor	Terrazzo	-	-	Non ACM	-	-	-	-	
813	Corridor - 1972	Wall	Plaster	-	-	Non ACM	SL	S02cde	-	ND	
813	Corridor - 1972	Ceiling	Ceiling Tile 2' x 2'	Large Pinhole (Drywall)	-	Non ACM	-	-	-	-	
813	Corridor - 1972	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole (2013)	-	Non ACM	-	-	-	-	
813	Corridor - 1972	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-	
813	Corridor - 1972	Firespray	Firespray	Spray-applied	F	ACM	HM	S06	10-Mar-08	4.1% Chrysotile	
813	Corridor - 1966	Floor	Terrazzo	-	-	Non ACM	-	-	-	-	
813	Corridor - 1966	Wall	Plaster	-	-	Non ACM	SL	S05abcd	10-Mar-08	ND	
813	Corridor - 1966	Ceiling	Ceiling Tile 2' x 2'	Large Pinhole (Drywall)	-	Non ACM	-	-	-	-	
813	Corridor - 1966	Ceiling	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-	
813	Corridor - 1966	Firespray	Firespray	-	F	ACM	SL	S06abc	10-Mar-08	4.1% Chrysotile	
813	Corridor - 1966	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
813	Corridor - 1962	Floor	Terrazzo	-	-	Non ACM	-	-	-	-	
813	Corridor - 1962	Wall	Plaster	-	-	Non ACM	SL	S19abcde	10-Mar-08	ND	
813	Corridor - 1962	Ceiling	Ceiling Tile 2' x 2'	Large Pinhole (Drywall)	-	Non ACM	-	-	-	-	


		School Name		Legend:					Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable					All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:							Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955									
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011									
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type	
813	Corridor - 1962	Ceiling	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-	
813	Corridor - 1962	Firespray	Firespray	-	F	ACM	SL	S06abc	10-Mar-08	4.1% Chrysotile	
813	Corridor - 1962	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
814	Corridor	Floor	Terrazzo	-	-	Non ACM	-	-	-	-	
814	Corridor	Wall	Concrete	-	-	Non ACM	-	-	-	-	
814	Corridor	Wall	Ceramic Tile	-	-	Non ACM	-	-	-	-	
814	Corridor	Ceiling	Ceiling Tile 1' x 1'	Large and Small	-	Non ACM	HM	S10	10-Mar-08	ND	
814	Corridor	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
815	Corridor	Floor	Vinyl Floor Tile 9"x 9"	Tan with White & Black Fleck	NF	ACM	HM	S26	13-Mar-08	0.75% Chrysotile	
815	Corridor	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND	
815	Corridor	Wall	Concrete	-	-	Non ACM	-	-	-	-	
815	Corridor	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Pinhole	NF	ACM	HM	S12	10-Mar-08	2.1% Amosite	
816	Corridor	Floor	Vinyl Floor Tile 12"x 12"	White with Grey Fleck (Post 2010)	-	Non ACM	-	-	-	-	
816	Corridor	Wall	Concrete	-	-	Non ACM	-	-	-	-	
816	Corridor	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND	
816	Corridor	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
818	Corridor	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	HM	S30	13-Mar-08	5.0% Chrysotile	
818	Corridor	Wall	Concrete	-	-	Non ACM	-	-	-	-	
818	Corridor	Ceiling	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND	
818	Corridor	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-	
818	Corridor	Above Ceiling	Texture Coat	-	F	ACM	HM	S39	13-Mar-08	20% Chrysotile	
819	Corridor	Floor	Vinyl Floor Tile 12"x 12"	Grey with Brown & White Fleck	-	Non ACM	HM	S37	13-Mar-08	ND	
819	Corridor	Wall	Concrete	-	-	Non ACM	-	-	-	-	
819	Corridor	Ceiling	Ceiling Tile 2' x 2'	Solid Pattern	-	Non ACM	HM	S38	13-Mar-08	ND	
819	Corridor	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-	
820	Corridor	Floor	Concrete	-	-	Non ACM	-	-	-	-	
820	Corridor	Wall	Concrete	-	-	Non ACM	-	-	-	-	
820	Corridor	Wall	Brick	-	-	Non ACM	-	-	-	-	
820	Corridor	Deck	Concrete	-	-	Non ACM	-	-	-	-	
820	Corridor	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile	
830	Corridor	Floor	Vinyl Floor Tile 12"x 12"	Grey Oatmeal	-	Non ACM	HM	S90	13-Mar-08	ND	
830	Corridor	Wall	Plaster	-	-	Non ACM	HM	S64, S82	10-Mar-08	ND	


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
830	Corridor	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
830	Corridor	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (1997)	-	Non ACM	-	-	-	-
830	Corridor	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
901	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
901	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
901	Stairwell	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
901	Stairwell	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
902	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
902	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
902	Stairwell	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
902	Stairwell	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
903	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
903	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
903	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
903	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
904	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
904	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
904	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
904	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
905	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
905	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
905	Stairwell	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	10-May-18	ND
905	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
905	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
905	Stairwell	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S77	10-May-18	ND
905	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
905	Stairwell	Wall	Plaster	-	-	Non ACM	SL	S35abcd	13-Mar-08	ND
905	Stairwell	Ceiling	Ceiling Tile 2' x 2'	Dense Fissure Small Pinhole	-	Non ACM	SL	S29abc	13-Mar-08	ND
905	Stairwell	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (Post 1994)	-	Non ACM	-	-	-	-
905A	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
905A	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
905A	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
905A	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S24, S72, S82	13-Mar-08	ND
905A	Stairwell	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
905A	Stairwell	Piping	Pipe Fitting	Fibreglass/PVC	-	Non ACM	-	-	-	-
906	Stairwell	Floor	Vinyl Floor Tile 12"x 12"	Orange with White Fleck	NF	ACM	SL	S30abc	13-Mar-08	5.0% Chrysotile
906	Stairwell	Floor	Vinyl Floor Tile 12"x 12"	Beige with Grey Fleck	NF	ACM	SL	S31abc	13-Mar-08	5.0% Chrysotile
906	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
906	Stairwell	Ceiling	Ceiling Tile 2' x 2'	Dense Fissure Small Pinhole	-	Non ACM	SL	S29abc	13-Mar-08	ND
906	Stairwell	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
907	Stairwell	Floor	Concrete	-	-	Non ACM	-	-	-	-
907	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
907	Stairwell	Ceiling	Concrete	-	-	Non ACM	-	-	-	-
908	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
908	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND
908	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
908	Stairwell	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	SL	S04abc	10-Mar-08	ND
908	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND
908A	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
908A	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND
908A	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
908A	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND
909	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
909	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S02	10-Mar-08	ND
909	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
909	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S02	10-Mar-08	ND
909	Stairwell	Ceiling	Ceiling Tile 2' x 2'	Large Pinhole (Drywall)	-	Non ACM	-	-	-	-
909	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
909	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S35	-	-
909	Stairwell	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
Level 2										
118	Washroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
118	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
118	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S72	13-Mar-08	ND
118A	Custodial Room	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
118A	Custodial Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
118A	Custodial Room	Ceiling	Plaster	-	-	Non ACM	HM	S72	13-Mar-08	ND
120	Washroom	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
120	Washroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
120	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S72	13-Mar-08	ND
120A	Fan Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
120A	Fan Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
120A	Fan Room	Deck	Concrete	-	-	Non ACM	-	-	-	-
120A	Fan Room	Fireproofing	Fireproofing	Troweled-Applied	F	ACM	SL	S01abc	3-Oct-22	40% Chrysotile
120A	Fan Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
120A	Fan Room	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
120A	Fan Room	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
121	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Beige Dense Fleck (Post 2013)	-	Non ACM	-	-	-	-
121	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
121	Classroom	Wall	Plaster	-	-	Non ACM	HM	S72	13-Mar-08	ND
121	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
121	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
122	Classroom	Floor	Vinyl Sheet Flooring	New (2021)	-	Non ACM	-	-	-	-
122	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
122	Classroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
122	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
122	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
123	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Olive with Black Streak	NF	ACM	SL	S11ABC	10-May-18	1% Chrysotile
123	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
123	Classroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
123	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
123	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
124	Classroom	Floor	Vinyl Sheet Flooring	New (2021)	-	Non ACM	-	-	-	-
124	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-


		School Name		Legend:					Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable					All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:							Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955									
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011									
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type	
124	Classroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND	
124	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-	
124	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-	
125	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Green with Faded Streak	NF	ACM	SL	S76abc	13-Mar-08	1.4% Chrysotile	
125	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
125	Classroom	Wall	Plaster	-	-	Non ACM	SL	S72de	13-Mar-08	ND	
125	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-	
125	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-	
126	Classroom	Floor	Vinyl Sheet Flooring	New (2021)	-	Non ACM	-	-	-	-	
126	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
126	Classroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND	
126	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-	
126	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-	
127	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Beige with Brown & White Fleck	NF	ACM	SL	S75abc	13-Mar-08	1.5% Chrysotile	
127	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
127	Classroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND	
127	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-	
127	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-	
128	Classroom	Floor	Vinyl Sheet Flooring	New (2021)	-	Non ACM	-	-	-	-	
128	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
128	Classroom	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND	
128	Classroom	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-	
128	Classroom	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-	
520	Washroom	Floor	Vinyl Floor Tile 12"x 12"	Beige with Beige Fleck	-	Non ACM	SL	S57abc	10-Mar-08	ND	
520	Washroom	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND	
520	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND	
520A	Custodial Closet	Floor	Vinyl Floor Tile 12"x 12"	Grey with Grey and White Spots	-	Non ACM	SL	S58abc	10-Mar-08	ND	
520A	Custodial Closet	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND	
520A	Custodial Closet	Wall	Wood	-	-	Non ACM	-	-	-	-	
520A	Custodial Closet	Ceiling	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND	
521	Computer Room	Floor	Vinyl Floor Tile 9"x 9"	Green with White Streaks	NF	ACM	SL	S21abc	10-Mar-08	0.5% Chrysotile	
521	Computer Room	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND	


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
521	Computer Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
521	Computer Room	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
521A	Office	Floor	Vinyl Floor Tile 9"x 9"	Green with White Streaks	NF	ACM	HM	S21	10-Mar-08	0.5% Chrysotile
521A	Office	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
521A	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
521A	Office	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND
522	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Blue with White Fleck	NF	ACM	HM	S20	10-Mar-08	0.5% Chrysotile
522	Classroom	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
522	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
522	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
523	Computer Room	Floor	Vinyl Floor Tile 9"x 9"	Green with White Streaks	NF	ACM	HM	S21	10-Mar-08	0.5% Chrysotile
523	Computer Room	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
523	Computer Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
523	Computer Room	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
524	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Olive/Green/Grey with White Streaks	NF	ACM	SL	S56abc	10-Mar-08	-
524	Classroom	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
524	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
524	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
525	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Blue with White Streaks	NF	ACM	HM	S20	10-Mar-08	0.5% Chrysotile
525	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
525	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
525	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
526	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Red/Brown with White and Brown Streaks	NF	ACM	SL	S55abc	10-Mar-08	1.4% Chrysotile
526	Classroom	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
526	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
526	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
527	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Dark Grey/Brown with Brown and White	NF	ACM	SL	S52abc	10-Mar-08	1.2% Chrysotile
527	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
527	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
527	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
528	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Green with White Streaks	NF	ACM	SL	S21abc	10-Mar-08	0.5% Chrysotile
528	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND


		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
528	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
528	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
530	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Brown with White and Brown Spots	-	Non ACM	SL	S53abc	10-Mar-08	ND
530	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
530	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
530	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
530	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND
531	Storage	Floor	Vinyl Floor Tile 12"x 12"	Brown with White and Brown Spots	-	Non ACM	SL	S53abc	10-Mar-08	ND
531	Storage	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
531	Storage	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND
532	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Brown Dense Fleck (Post 2010)	-	Non ACM	-	-	-	-
532	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
532	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
532	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
532	Classroom	Ceiling	Ceiling Tile 1' x 1'	Medium and Small Hole (Cellulose)	-	Non ACM	-	-	-	-
533	Office	Floor	Vinyl Floor Tile 9"x 9"	Grey/Tan with White	NF	ACM	SL	S51abc	10-Mar-08	1.4% Chrysotile
533	Office	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
533	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
533	Office	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND
533A	Staff Work Room	Floor	Vinyl Floor Tile 9"x 9"	Tan with Red and Black	NF	ACM	SL	S28abc	10-Mar-08	4.1% Chrysotile
533A	Staff Work Room	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
533A	Staff Work Room	Wall	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
533A	Staff Work Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
533A	Staff Work Room	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND
533A	Staff Work Room	Ceiling	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
533B	Washroom	Floor	Vinyl Floor Tile 9"x 9"	Tan with Red and Black	NF	ACM	SL	S28abc	10-Mar-08	4.1% Chrysotile
533B	Washroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
533B	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
533C	Washroom	Floor	Vinyl Floor Tile 9"x 9"	Tan with Red and Black	NF	ACM	SL	S28abc	10-Mar-08	4.1% Chrysotile
533C	Washroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
533C	Washroom	Ceiling	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
534	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Dark Green with Green and White	NF	ACM	SL	S49abc	10-Mar-08	0.75% Chrysotile

		School Name		Legend:					Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable					All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:							Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955									
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011									
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type	
534	Classroom	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND	
534	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
534	Classroom	Ceiling	Ceiling Tile 2' x 4'	Dense Short Fissure Random Pinhole	-	Non ACM	SL	S50abc	10-Mar-08	ND	
534	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND	
535	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Tan with Red and Black	NF	ACM	SL	S28abc	10-Mar-08	4.1% Chrysotile	
535	Classroom	Wall	Plaster	-	-	Non ACM	HM	S02	10-Mar-08	ND	
535	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
535	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
535	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND	
536	Classroom	Floor	Vinyl Floor Tile 9"x 9"	Light Brown with Brown and White	NF	ACM	SL	S48abc	10-Mar-08	1.2% Chrysotile	
536	Classroom	Wall	Plaster	-	-	Non ACM	HM	S02	10-Mar-08	ND	
536	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
536	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
536	Classroom	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND	
537	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Tan/Olive with White and Brown	NF	ACM	SL	S46abc	-	-	
537	Classroom	Wall	Drywall	Drywall Joint Compound	-	Non ACM	HM	S01	-	-	
537	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-	
537	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2000)	NF	Non ACM		-	-	-	
537	Classroom	Ceiling	Ceiling Tile 1' x 1'	Thick Fissure Small Pinhole	-	Non ACM	HM	S45	10-Mar-08	ND	
537A	Office	Floor	Vinyl Floor Tile 9"x 9"	Tan with Red and Black	NF	ACM	SL	S28abc	10-Mar-08	4.1% Chrysotile	
537A	Office	Wall	Plaster	-	-	Non ACM	HM	S02	10-Mar-08	ND	
537A	Office	Wall	Concrete	-	-	Non ACM	-	-	-	-	
537A	Office	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
537A	Office	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND	
537B	Show Room	Floor	Carpet	-	-	Non ACM	-	-	-	-	
537B	Show Room	Wall	Plaster	-	-	Non ACM	HM	S02	10-Mar-08	ND	
537B	Show Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
537C	Kiln Room	Floor	Vinyl Floor Tile 9"x 9"	Tan with Red and Black	NF	ACM	HM	S28	10-Mar-08	4.1% Chrysotile	
537C	Kiln Room	Wall	Plaster	-	-	Non ACM	HM	S02	10-Mar-08	ND	
537C	Kiln Room	Wall	Concrete	-	-	Non ACM	-	-	-	-	
537C	Kiln Room	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND	
537C	Kiln Room	Ceiling	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-	

		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
538	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Orange/Red with White	NF	ACM	SL	S30abc	10-Mar-08	5.0% Chrysotile
538	Classroom	Wall	Drywall	Drywall Joint Compound	-	Non ACM	HM	S01	-	-
538	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
538	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2000)	NF	Non ACM		-	-	-
538	Classroom	Ceiling	Ceiling Tile 1' x 1'	Thick Fissure Small Pinhole	-	Non ACM	HM	S45	10-Mar-08	ND
539	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Tan/Olive with White and Brown	NF	ACM	SL	S46abc	-	-
539	Classroom	Wall	Drywall	Drywall Joint Compound	-	Non ACM	HM	S01	-	-
539	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
539	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2000)	NF	Non ACM		-	-	-
539	Classroom	Ceiling	Ceiling Tile 1' x 1'	Thick Fissure Small Pinhole	-	Non ACM	HM	S45	10-Mar-08	ND
540	Classroom	Floor	Vinyl Floor Tile 12"x 12"	Olive and White	NF	ACM	SL	S44abc	10-Mar-08	2.4% Chrysotile
540	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
540	Classroom	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole (2000)	NF	Non ACM		-	-	-
540	Classroom	Ceiling	Ceiling Tile 1' x 1'	Thick Fissure Small Pinhole	-	Non ACM	SL	S45abc	10-Mar-08	ND
550	Classroom	Floor	Concrete	-	-	Non ACM	-	-	-	-
550	Classroom	Wall	Concrete	-	-	Non ACM	-	-	-	-
550	Classroom	Ceiling	Metal Pan	-	-	Non ACM	-	-	-	-
550	Classroom	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
550	Classroom	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
551	Projection Room	Floor	Vinyl Floor Tile 12"x 12"	Brown with Brown and White Fleck	-	Non ACM	HM	S53	13-Mar-08	ND
551	Projection Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
551	Projection Room	Ceiling	Ceiling Tile 2' x 2'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
554	Fan Room (Above 555)	Floor	Concrete	-	-	Non ACM	-	-	-	-
554	Fan Room (Above 555)	Wall	Concrete	-	-	Non ACM	-	-	-	-
554	Fan Room (Above 555)	Ceiling	Metal Pan	-	-	Non ACM	-	-	-	-
554	Fan Room (Above 555)	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
554	Fan Room (Above 555)	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
555	Equipment Storage	Floor	Concrete	-	-	Non ACM	-	-	-	-
555	Equipment Storage	Wall	Concrete	-	-	Non ACM	-	-	-	-
555	Equipment Storage	Wall	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-
555	Equipment Storage	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
556	Fly Gallery	Floor	Concrete	-	-	Non ACM	-	-	-	-

		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
556	Fly Gallery	Wall	Concrete	-	-	Non ACM	-	-	-	-
556	Fly Gallery	Ceiling	Metal Pan	-	-	Non ACM	-	-	-	-
556	Fly Gallery	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
556	Fly Gallery	Wall	Transite	Asbestos Cement Board	NF	ACM	VC			
557	Mechanical Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
557	Mechanical Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
557	Mechanical Room	Ceiling	Plaster	-	-	Non ACM	SL	S60abc	10-Mar-08	ND
557	Mechanical Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
557	Mechanical Room	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
557	Mechanical Room	Piping	Pipe Insulation	Air Cell	F	ACM	HM	1680.894.04	11-Sep-90	>75% Amosite
558	Duct Space	Floor	Concrete	-	-	Non ACM	-	-	-	-
558	Duct Space	Wall	Concrete	-	-	Non ACM	-	-	-	-
558	Duct Space	Wall	Brick	-	-	Non ACM	-	-	-	-
558	Duct Space	Ceiling	Metal Pan	-	-	Non ACM	-	-	-	-
558	Duct Space	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	SL	S61abc	10-Mar-08	1.3% Chrysotile
558	Duct Space	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
558	Duct Space	-	Texture Coat	Grey	-	Non ACM	SL	S62abc	10-Mar-08	ND
559	Washroom	Floor	Vinyl Floor Tile 12"x 12"	Beige with Beige Fleck	-	Non ACM	HM	S57	10-Mar-08	ND
559	Washroom	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
559	Washroom	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	HM	S13	10-May-18	ND
560	Nurse's Office	Floor	Vinyl Floor Tile 9"x 9"	Grey with White and Grey Streaks	NF	ACM	HM	S59	10-Mar-08	1.5% Chrysotile
560	Nurse's Office	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
560	Nurse's Office	Wall	Plaster	-	-	Non ACM	HM	S27	10-Mar-08	ND
561	Fan Room	Floor	Concrete	-	-	Non ACM	-	-	-	-
561	Fan Room	Wall	Concrete	-	-	Non ACM	-	-	-	-
561	Fan Room	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
561	Fan Room	Ceiling	Metal Pan	-	-	Non ACM	-	-	-	-
561	Fan Room	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
561	Fan Room	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
821	Corridor - 1966 Addition	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
821	Corridor - 1966 Addition	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
821	Corridor - 1966 Addition	Ceiling	Ceiling Tile 2 x 2	Short Fissure Random Pinhole	NF	ACM		-	-	-

		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
821	Corridor - 1966 Addition	Ceiling	Ceiling Tile 2' x 2'	Large & Small Pinhole (Drywall)	-	Non ACM	-	-	-	-
821	Corridor - 1966 Addition	Above Ceiling	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-
821	Corridor - 1966 Addition	Firespray	Firespray	Colour Sprayed Applied (2021)	-	Non ACM	-	-	-	-
821	Corridor - 1966 Addition	Wall Cavities	Firespray	Sprayed Applied	F	ACM	HM	S06	13-Mar-08	4.1% Chrysotile
822	Corridor near 561	Floor	Vinyl Floor Tile 9"x 9"	Grey with White and Grey Streaks	NF	ACM	SL	S59abc	10-Mar-08	1.5% Chrysotile
822	Corridor near 561	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
822	Corridor near 561	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
823	Corridor - 1962	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
823	Corridor - 1962	Wall	Plaster	-	-	Non ACM	HM	S19	10-Mar-08	ND
823	Corridor - 1962	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
823	Corridor - 1962	Ceiling	Ceiling Tile 2' x 4'	Textured Pinhole	-	Non ACM	SL	S54abc	10-Mar-08	ND
823	Corridor - 1962	Piping	Pipe Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
823	Corridor - 1962	Piping	Pipe Fitting	Parged Cement	F	ACM	HM	1680.894.03	11-Sep-90	50-75% Chrysotile
824	Corridor - 1972	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
824	Corridor - 1972	Wall	Plaster	-	-	Non ACM	HM	S02	10-Mar-08	ND
824	Corridor - 1962	Ceiling	Ceiling Tile 1' x 1'	Large/Medium Pinhole	-	Non ACM	SL	S13ABC	10-May-18	ND
824	Corridor - 1972	Ceiling	Ceiling Tile 2' x 4'	Short Fissure Random Pinhole	-	Non ACM	HM	S01	10-May-18	ND
824	Corridor - 1966	Ceiling	Drywall	No Drywall Joint Compound	-	Non ACM	-	-	-	-
824	Corridor - 1966	Firespray	Firespray	Troweled-applied	F	ACM	SL	S06abc	10-Mar-08	4.1% Chrysotile
824	Corridor - 1972	Ducting	Duct Insulation	Fiberglass insulation	-	Non ACM	-	-	-	-
824	Corridor - 1972	Ducting	Flex Joint	-	NF	ACM	VC	-	-	-
901	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
901	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
901	Stairwell	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
901	Stairwell	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
902	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
902	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S72, S82	13-Mar-08	ND
902	Stairwell	Ceiling	Ceiling Tile 2' x 4'	Random Fissure Random Pinhole (2021)	-	Non ACM	-	-	-	-
902	Stairwell	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S81	10-Mar-08	1% Chrysotile
903	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
903	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
903	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND

		School Name		Legend:				Notes:		
		Waterloo-Oxford District Secondary School		HM - Homogenous Material - homogeneous with previously sampled material SL - Sample Location - Material Sampled VC - Visually Confirmed - Material not sampled, deemed ACM NF - Non-Friable F- Friable				All quantities provided on Figures, if known. Refer to the Asbestos Audit Update Report for condition of ACM and recommended actions.		
		Date Built:						Dates provided in Material Description/Room Description columns indicates date of installation/renovation and confirms the finishes as non-ACM.		
		Original: 1955								
		Addition(s): 1958, 1962, 1966, 1971, 1972, 2000, 2001, 2011								
WRDSB Fixed Reference Number	Room Description	Inspected Item	Inspected Material	Material Description	Friability	Asbestos Classification	Sample / Identification Summary	Sample ID	Sample Date	% Asbestos & Fibre Type
903	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
904	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
904	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
904	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
904	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S82	13-Mar-08	ND
906	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
906	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
906	Stairwell	Ceiling	Ceiling Tile 2' x 2'	Dense Fissure Small Pinhole	-	Non ACM	SL	S29abc	13-Mar-08	ND
906	Stairwell	Piping	Pipe Insulation	Fibreglass insulation	-	Non ACM	-	-	-	-
907	Stairwell	Floor	Vinyl Floor Tile 12"x 12"	Grey Dense Fleck (Post 2010)	-	Non ACM	-	-	-	-
907	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
907	Stairwell	Ceiling	Drywall	Drywall Joint Compound	NF	ACM	HM	S61	10-Mar-08	1.3% Chrysotile
908	Stairwell	Floor	Terrazzo	-	-	Non ACM	-	-	-	-
908	Stairwell	Wall	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND
908	Stairwell	Wall	Concrete	-	-	Non ACM	-	-	-	-
908	Stairwell	Ceiling	Ceiling Tile 1' x 1'	Large and Small Pinhole	-	Non ACM	HM	S04abc	10-Mar-08	ND
908	Stairwell	Ceiling	Plaster	-	-	Non ACM	HM	S24, S43	10-Mar-08	ND
Summary of Potential ACM Hidden or Not Assessed										
300	Boiler Room	Boiler Refractory	Not Inspected							
	Throughout Building	Not Inspected	Not Inspected	Wall Cavity Insulation						
	Throughout Building	Not Inspected	Not Inspected	Door Core Insulation						

Appendix B

Figures

For Tender Purposes

***REFER TO **APPENDIX A: ASBESTOS MANAGEMENT DATABASE** FOR FULL LIST OF ASBESTOS-CONTAINING MATERIALS (ACM).
***ALL ACM MAY NOT BE DEPICTED IN THIS FIGURE.

NOTES:
ALL DRAWINGS TO BE REFERENCED WITH THE ASSOCIATED REPORT. LOCATIONS AND QUANTITIES ARE APPROXIMATE.
ALL KNOWN OR SUSPECT ASBESTOS-CONTAINING MATERIALS AND/OR DESIGNATED MATERIALS ARE NOT DEPICTED ON THIS DRAWING. REFER TO THE REPORT FOR A COMPLETE LIST OF IDENTIFIED MATERIALS.
THIS FIGURE IS COLOUR DEPENDENT. PHOTOCOPIES MAY ALTER INTERPRETATION OF THE FIGURE. ALWAYS REFER TO ORIGINAL DRAWINGS AND REPORT.

Legend
13 Fixed Reference Number
No Access
Post 1986 Construction

Asbestos-Containing Materials (ACM):
Floor Tile
Rolled Flooring
Ceiling Tile (Ceiling Surface)
Ceiling Tile (Located Above Drop Ceiling)
Friable Soft Textured Ceiling
Non-Friable Hard Textured Ceiling
Spray-On Fire Proofing
Trowel Applied Fire Proofing
Transite (Asbestos Cement) Paneling
Duct Insulation
Pipe Fitting Insulation w Quantity (Brackets Indicate # of Damaged Fittings)
Pipe Insulation (Vertical and Horizontal)
Transite (Asbestos Cement) Pipe (Vertical and Horizontal)
Duct Expansion Joints w Quantity (Brackets Indicate # of Damaged Joints)
Friable Debris




CLIENT
WATERLOO REGION DISTRICT SCHOOL BOARD


PROJECT
2021 ASBESTOS AUDIT UPDATE

DRAWING
WATERLOO-OXFORD DISTRICT SECONDARY SCHOOL
LEVEL ONE

Project Manager	P. Semeniuk	Date	October 2022 Revision
Design By	WRDSB	Project No.	34532-921
Drawn By	P. Semeniuk	Drawing No.	1.0
Scale	N.T.S.		



***REFER TO **APPENDIX A: ASBESTOS MANAGEMENT DATABASE** FOR FULL LIST OF ASBESTOS-CONTAINING MATERIALS (ACM).
***ALL ACM MAY NOT BE DEPICTED IN THIS FIGURE.



NOTES:
ALL DRAWINGS TO BE REFERENCED WITH THE ASSOCIATED REPORT. LOCATIONS AND QUANTITIES ARE APPROXIMATE.
ALL KNOWN OR SUSPECT ASBESTOS-CONTAINING MATERIALS AND/OR DESIGNATED MATERIALS ARE NOT DEPICTED ON THIS DRAWING. REFER TO THE REPORT FOR A COMPLETE LIST OF IDENTIFIED MATERIALS.
THIS FIGURE IS COLOUR DEPENDENT. PHOTOCOPIES MAY ALTER INTERPRETATION OF THE FIGURE. ALWAYS REFER TO ORIGINAL DRAWINGS AND REPORT.

- Legend**
- 13 Fixed Reference Number
 - No Access
 - Post 1986 Construction

- Asbestos-Containing Materials (ACM):**
- Floor Tile
 - Rollled Flooring
 - Ceiling Tile
 - Friable Soft Textured Ceiling
 - Non-Friable Hard Textured Ceiling
 - Spray-On Fire Proofing
 - Trowel Applied Fire Proofing
 - Transite (Asbestos Cement) Paneling
 - Duct Insulation
 - Pipe Fitting Insulation w Quantity (Brackets Indicate # of Damaged Fittings)
 - Pipe Insulation (Vertical and Horizontal)
 - Transite (Asbestos Cement) Pipe (Vertical and Horizontal)
 - Duct Expansion Joints w Quantity (Brackets Indicate # of Damaged Joints)
 - Friable Debris

MTE
Ph. (519) 743-6500 www.mte85.com

CLIENT
WATERLOO REGION
DISTRICT SCHOOL BOARD

PROJECT
2021 ASBESTOS
AUDIT UPDATE

DRAWING
WATERLOO-OXFORD
DISTRICT SECONDARY SCHOOL
LEVEL TWO

Project Manager	P. Semeniuk	Date	October 2022 Revision
Design By	WRDSB	Project No.	34532-921
Drawn By	P. Semeniuk	Drawing No.	2.0
Scale	N.T.S.		

Appendix C

Tables

For Tender Purposes









TABLE 1 - INTERNAL ABATEMENT MANAGEMENT						
Waterloo Oxford Secondary School						
Material	WRDSB Fixed Reference Number	Material Description	Approximate Quantity	Photograph - Context	Photograph - Detail	Required Action
Asbestos Non-Friable	103	9" x 9" Tan Floor Tile	2 tiles			Monitor Annually
Asbestos Non-Friable	125	9" x 9" Green Floor Tile	5 Tiles			Monitor Annually
Asbestos Non-Friable	200	Drywall	<1 m ²			Monitor Annually
Asbestos Non-Friable	200	Drywall	<1 m ²			Monitor Annually

Table 1 and 2 - Damaged Materials - Waterloo Oxford District Secondary School








TABLE 1 - INTERNAL ABATEMENT MANAGEMENT						
Waterloo Oxford Secondary School						
Material	WRDSB Fixed Reference Number	Material Description	Approximate Quantity	Photograph - Context	Photograph - Detail	Required Action
Asbestos Non-Friable	207	12"x12" beige Floor Tiles cracking and degrading at floor seam	40 tiles			Removal in accordance with O. Reg. 278/05 as a Type 1 Operation
Asbestos Non-Friable	101, 102, 102A, 102B, 103, 103C, 103F, 104, 122, 124, 126, 128	1' x 1' Ceiling Tiles - Damage at hangers and penetrations	Throughout			Monitor Annually
Asbestos Non-Friable	404B	1' x 1' Ceiling Tiles	19 tiles			Removal in accordance with O. Reg. 278/05 as a Type 1 Operation
Asbestos Non-Friable	802 at room 206	Drywall	<1 m ²			Monitor Annually

Table 1 and 2 - Damaged Materials - Waterloo Oxford District Secondary School









TABLE 1 - INTERNAL ABATEMENT MANAGEMENT						
Waterloo Oxford Secondary School						
Material	WRDSB Fixed Reference Number	Material Description	Approximate Quantity	Photograph - Context	Photograph - Detail	Required Action
Asbestos Non-Friable	807B	12"x12" orange Floor Tiles	3 Tiles			Monitor Annually
Asbestos Non-Friable	809	2' x 2' Ceiling Tiles - Dense Fissure Random Pinhole	15+ Tiles			Removal in accordance with O. Reg. 278/05 as a Type 1 Operation
Asbestos Non-Friable	822	Exposed Mastic	14 tiles			Repair/Removal in accordance with O. Reg. 278/05 as a Type 1 Operation
Asbestos Non-Friable	906	12"x12" orange Floor Tiles	2 Tiles			Monitor Annually

Table 1 and 2 - Damaged Materials - Waterloo Oxford District Secondary School

TABLE 1 - INTERNAL ABATEMENT MANAGEMENT						
Waterloo Oxford Secondary School						
Material	WRDSB Fixed Reference Number	Material Description	Approximate Quantity	Photograph - Context	Photograph - Detail	Required Action
<div>Notes:</div> <div>1) A copy of this report should be provided to all prospective contractors prior to tender or quotation, in accordance with Section 30 of the Occupational Health and Safety Act.</div> <div>2) Recommended actions are the minimum required actions, as prescribed by the appropriate Acts, regulations, guidelines, standards, codes and general best practice measures. The Contractor may choose to alter the approach and combine or break out sections of work. This is acceptable provided that the appropriate Acts, regulations, guidelines, standards and codes are followed and afford protection for the health and safety of workers, occupants and the public that is at least equal to the protection that would be provided by complying with the minimum requirements.</div> <div>3) All waste generated is subject to characterization and disposal in accordance with Ontario Regulation 347.</div>						









TABLE 2 - EXTERNAL ABATEMENT MANAGEMENT						
Waterloo Oxford Secondary School						
Material	WRDSB Fixed Reference Number	Material Description	Approximate Quantity	Photograph - Context	Photograph - Detail	Required Action
Asbestos Friable	104B	Insulation on Pipe Fittings	2			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation
Asbestos Friable	300	Insulation on Pipe Fittings	2			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation
Asbestos Friable	300	Insulation on Pipe Fittings	1			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation
Asbestos Friable	300	Insulation on Pipe Fittings	1			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation

Table 1 and 2 - Damaged Materials - Waterloo Oxford District Secondary School









TABLE 2 - EXTERNAL ABATEMENT MANAGEMENT						
Waterloo Oxford Secondary School						
Material	WRDSB Fixed Reference Number	Material Description	Approximate Quantity	Photograph - Context	Photograph - Detail	Required Action
Asbestos Friable	300	Insulation on Pipe Fittings	1			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation
Asbestos Friable	300	Insulation on Pipe Fittings	2			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation
Asbestos Friable	300	Insulation on Pipe Fittings	1			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation
Asbestos Friable	300	Insulation on Pipe Fittings	1			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation

Table 1 and 2 - Damaged Materials - Waterloo Oxford District Secondary School





TABLE 2 - EXTERNAL ABATEMENT MANAGEMENT						
Waterloo Oxford Secondary School						
Material	WRDSB Fixed Reference Number	Material Description	Approximate Quantity	Photograph - Context	Photograph - Detail	Required Action
Asbestos Friable	300	Insulation on Pipe Fittings	1			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation
Asbestos Non-Friable	518	2" x4" Ceiling Tiles	30+ Tiles			Removal in accordance with O. Reg. 278/05 as a Type 2 Operation
<p>Notes:</p> <p>1) A copy of this report should be provided to all prospective contractors prior to tender or quotation, in accordance with Section 30 of the Occupational Health and Safety Act.</p> <p>2) Recommended actions are the minimum required actions, as prescribed by the appropriate Acts, regulations, guidelines, standards, codes and general best practice measures. The Contractor may choose to alter the approach and combine or break out sections of work. This is acceptable provided that the appropriate Acts, regulations, guidelines, standards and codes are followed and afford protection for the health and safety of workers, occupants and the public that is at least equal to the protection that would be provided by complying with the minimum requirements.</p> <p>3) All waste generated is subject to characterization and disposal in accordance with Ontario Regulation 347.</p>						

Table 1 and 2 - Damaged Materials - Waterloo Oxford District Secondary School

TABLE 3: BULK ASBESTOS SAMPLING SUMMARY					
Sample #	WRDSB Fixed Reference Number	Material Description	Asbestos Content (%)	Fibre Type	Is Material ACM
2008 Asbestos Audit Update					
32523-WOHS S01A	518	Drywall - Joint Compound	ND	-	No
32523-WOHS S01B			ND	-	No
32523-WOHS S01C			ND	-	No
32523-WOHS S02A	518	Plaster - White/Off-White	ND	-	No
32523-WOHS S02B			ND	-	No
32523-WOHS S02C			ND	-	No
32523-WOHS S02D	513		ND	-	No
32523-WOHS S02E			ND	-	No
32523-WOHS S03A	518	2' x 4' Ceiling Tile	1.7 0.6	Amosite Chrysotile	Yes
32523-WOHS S03B	518		NA	Amosite Chrysotile	Yes
32523-WOHS S03C	518		NA	Amosite Chrysotile	Yes
32523-WOHS S04A	908	1x1 Ceiling Tile - Large and Small Pinhole	ND	-	No
32523-WOHS S04B			ND	-	No
32523-WOHS S04C			ND	-	No
32523-WOHS S05A	513	Plaster - White/Off-White	ND	-	No
32523-WOHS S05B	513		ND	-	No
32523-WOHS S05C	513		ND	-	No
32523-WOHS S05D	513		ND	-	No
32523-WOHS S05E	509		ND	-	No
32523-WOHS S06A	513	Insulation - Fire Spray on beams and columns	4.1	Chrysotile	Yes
32523-WOHS S06B			NA	Chrysotile	Yes
32523-WOHS S06C			NA	Chrysotile	Yes
32523-WOHS S07A	516	Drywall - Joint Compound	1.8	Chrysotile	Yes
32523-WOHS S07B			1.7	Chrysotile	Yes
32523-WOHS S07C			1.8	Chrysotile	Yes
32523-WOHS S08A	516	Ceiling Finish - Texture Coat on Columns	ND	-	No
32523-WOHS S08B			ND	-	No
32523-WOHS S08C			ND	-	No
32523-WOHS S09A	515	9"x9" Floor Tile - Brown with White Fleck	Layer 1: 1.3 Layer 2: ND	Chrysotile	Yes
32523-WOHS S09B			Layer 1: NA Layer 2: ND	Chrysotile	Yes
32523-WOHS S09C			Layer 1: NA Layer 2: ND	Chrysotile	Yes
32523-WOHS S10A	509	1x1 Ceiling Tile - Large Pinhole	ND	-	No
32523-WOHS S10B			ND	-	No
32523-WOHS S10C			ND	-	No
32523-WOHS S11A	509	1x1 Ceiling Tile - Long Fissure Small Pinhole	ND	-	No
32523-WOHS S11B			ND	-	No
32523-WOHS S11C			ND	-	No
32523-WOHS S12A	516	1x1 Ceiling Tile - Medium and Small Pinhole	2.1	Amosite	Yes
32523-WOHS S12B			NA	Amosite	No
32523-WOHS S12C			NA	Amosite	No
32523-WOHS S13A	514A	2x4 Ceiling Tile - Random Fissure Random Pinhole	ND	-	No
32523-WOHS S13B			ND	-	No
32523-WOHS S13C			ND	-	No
32523-WOHS S14A	514A FE	1x1 Ceiling Tile - Acoustic Tile	ND	-	No
32523-WOHS S14B			ND	-	No
32523-WOHS S14C			ND	-	No
32523-WOHS S15A	514B – Staff Room	12"x12" Floor Tile - Tan with Brown	Layer 1: 3.6 Layer 2: ND	Chrysotile	Yes
32523-WOHS S15B			Layer 1: NA Layer 2: ND	Chrysotile	Yes
32523-WOHS S15C			Layer 1: NA Layer 2: ND	Chrysotile	Yes
32523-WOHS S16A	514B – Lunch Room	12"x12" Floor Tile - Tan with Grey/Brown Specks	ND	-	No
32523-WOHS S16B			ND	-	No
32523-WOHS S16C			ND	-	No
32523-WOHS S17A	512	2x4 Ceiling Tile - Long Fissure Random Pinhole	ND	-	No
32523-WOHS S17B			ND	-	No
32523-WOHS S17C			ND	-	No

Table 3 - Sample Summary Table - Waterloo Oxford District Secondary School

TABLE 3: BULK ASBESTOS SAMPLING SUMMARY					
Sample #	WRDSB Fixed Reference Number	Material Description	Asbestos Content (%)	Fibre Type	Is Material ACM
32523-WOHS S18A	512	9"x9" Floor Tile - Grey with White/Black	Layer 1: 1.8 Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S18B			Layer 1: NA Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S18C			Layer 1: NA Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S19A	513	Plaster - White with Tan Texture	ND	-	No
32523-WOHS S19B			ND	-	No
32523-WOHS S19C			ND	-	No
32523-WOHS S19D			ND	-	No
32523-WOHS S19E	801		ND	-	No
32523-WOHS S19F			ND	-	No
32523-WOHS S19G			ND	-	No
32523-WOHS S20A	506	9"x9" Floor Tile - Blue with White Streaks	Layer 1: 0.5 Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S20B			Layer 1: NA Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S20C			Layer 1: NA Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S21A	507	9"x9" Floor Tile - Green with White Streak	0.5	Chrysotile	Yes
32523-WOHS S21B			NA	Chrysotile	Yes
32523-WOHS S21C			NA	Chrysotile	Yes
32523-WOHS S22A	801	Insulation - Fire Spray on beams and columns	5.0	Chrysotile	Yes
32523-WOHS S22B			NA	Chrysotile	Yes
32523-WOHS S22C			NA	Chrysotile	Yes
32523-WOHS S23A	812	Insulation - Fire Spray on beams and columns	3.2	Chrysotile	Yes
32523-WOHS S23B			NA	Chrysotile	Yes
32523-WOHS S23C			NA	Chrysotile	Yes
32523-WOHS S24A	812	Plaster - White/Tan	ND	-	No
32523-WOHS S24B			ND	-	No
32523-WOHS S24C			ND	-	No
32523-WOHS S24D	404		ND	-	No
32523-WOHS S24E	811		ND	-	No
32523-WOHS S25A	405	9"x9" Floor Tile - Beige with Grey Fleck	Layer 1: Trace Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S25B			Layer 1: Trace Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S25C			Layer 1: Trace Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S26A	404	9"x9" Floor Tile - Tan with White/Black Fleck	Layer 1: 0.75 Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S26B			Layer 1: NA Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S26C			Layer 1: NA Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S27A	505-501	Plaster - White/Tan	ND	-	No
32523-WOHS S27B			ND	-	No
32523-WOHS S27C			ND	-	No
32523-WOHS S27D			ND	-	No
32523-WOHS S27E	502		ND	-	No
32523-WOHS S28A	501	9"x9" Floor Tile - Grey with White/Black/Red Fleck	Layer 1: 4.1 Layer 2: 1.9	Chrysotile Chrysotile	Yes -
32523-WOHS S28B			Layer 1: NA Layer 2: NA	Chrysotile Chrysotile	Yes -
32523-WOHS S28C			Layer 1: NA Layer 2: NA	Chrysotile Chrysotile	Yes -
32523-WOHS S29A	Stage Entrance	2x2 Ceiling Tile Deep Fissure Small Pinhole	ND	-	No
32523-WOHS S29B			ND	-	No
32523-WOHS S29C			ND	-	No
32523-WOHS S30A	Stage Entrance	12"x12" Floor Tile - Orange with White Fleck	Layer 1: 5.0 Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S30B			Layer 1: NA Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S30C			Layer 1: NA Layer 2: ND	Chrysotile -	Yes -
32523-WOHS S31A	Stage Entrance	12"x12" Floor Tile - Beige with Grey Fleck	ND	-	No
32523-WOHS S31B			ND	-	No
32523-WOHS S31C			ND	-	No

Table 3 - Sample Summary Table - Waterloo Oxford District Secondary School

TABLE 3: BULK ASBESTOS SAMPLING SUMMARY					
Sample #	WRDSB Fixed Reference Number	Material Description	Asbestos Content (%)	Fibre Type	Is Material ACM
32523-WOHS S32A	Cafeteria	12"x12" Floor Tile - Dark Beige with Brown/White Fleck	Layer 1: 0.25	Chrysotile	Yes
32523-WOHS S32B			Layer 2: 3.3	Chrysotile	Yes
32523-WOHS S32C			Layer 1: 0.5	Chrysotile	Yes
32523-WOHS S32C			Layer 2: NA	Chrysotile	Yes
32523-WOHS S33A	Cafeteria	Transite - Boards Cat Walk	Layer 1: NA	Chrysotile	Yes
32523-WOHS S33B			Layer 2: NA	Chrysotile	Yes
32523-WOHS S33C			35	Chrysotile	Yes
32523-WOHS S33C			NA	Chrysotile	Yes
32523-WOHS S34A	Dressing Room	12"x12" Floor Tile - Green wih Black/White/Grey Fleck	NA	Chrysotile	Yes
32523-WOHS S34B			Layer 1: 2.2	Chrysotile	Yes
32523-WOHS S34C			Layer 2: ND	-	-
32523-WOHS S34C			Layer 1: NA	Chrysotile	Yes
32523-WOHS S35A	905	Plaster	Layer 2: ND	-	-
32523-WOHS S35B			Layer 1: NA	Chrysotile	Yes
32523-WOHS S35C			Layer 2: ND	-	-
32523-WOHS S35D			Layer 1: NA	Chrysotile	Yes
32523-WOHS S35E	Cafeteria Hall		Layer 2: ND	-	-
32523-WOHS S36A	Cafeteria Hall	2' x 2' Ceiling Tile - Thin Fissure Small Pinhole	ND	-	No
32523-WOHS S36B			Sample not received	-	No
32523-WOHS S36C			Sample not received	-	No
32523-WOHS S37A			Sample not received	-	No
32523-WOHS S37B	Boys Washroom (near 502)	12"x12" Floor Tile - Grey with Brown/White Fleck	ND	-	No
32523-WOHS S37C			ND	-	No
32523-WOHS S38A			ND	-	No
32523-WOHS S38B			ND	-	No
32523-WOHS S38C	Servery	2' x 2' Ceiling Tile - Solid Pattern	ND	-	No
32523-WOHS S39A			ND	-	No
32523-WOHS S39B			20	Chrysotile	Yes
32523-WOHS S39C			NA	Chrysotile	Yes
32523-WOHS S40A	Back Storage	Ceiling Finish - Texture Coat/Fire Spray on Steel Deck Only	NA	Chrysotile	Yes
32523-WOHS S40B			NA	Chrysotile	Yes
32523-WOHS S40C			1.3	Chrysotile	Yes
32523-WOHS S40C			NA	Chrysotile	Yes
32523-WOHS S41A	Staff Dining	Plaster - White	NA	Chrysotile	Yes
32523-WOHS S41B			ND	-	No
32523-WOHS S41C			ND	-	No
32523-WOHS S42A			ND	-	No
32523-WOHS S42B	306	12"x12" Floor Tile - White with Black Fleck	ND	-	No
32523-WOHS S42C			ND	-	No
32523-WOHS S43A			ND	-	No
32523-WOHS S43B			ND	-	No
32523-WOHS S43C	307	Plaster - White/Grey	ND	-	No
32523-WOHS S44A			ND	-	No
32523-WOHS S44B			2.4	Chrysotile	Yes
32523-WOHS S44C			NA	Chrysotile	Yes
32523-WOHS S45A	540	12"x12" Floor Tile - Olive with White Streaks	NA	Chrysotile	Yes
32523-WOHS S45B			NA	Chrysotile	Yes
32523-WOHS S45C			ND	-	No
32523-WOHS S46A			ND	-	No
32523-WOHS S46B	540	1' x 1' Ceiling Tile - Thick Fissure Small Pinhole	ND	-	No
32523-WOHS S46C			ND	-	No
32523-WOHS S47A			ND	-	No
32523-WOHS S47B			ND	-	No
32523-WOHS S47C	537	12"x12" Floor Tile - Tan/Olive with White/Brown Specks	ND	-	No
32523-WOHS S48A			1.8	Chrysotile	Yes
32523-WOHS S48B			NA	Chrysotile	Yes
32523-WOHS S48C			NA	Chrysotile	Yes
32523-WOHS S49A	Kiln Room	Refractory - Inside of Kiln	ND	-	No
32523-WOHS S49B			ND	-	No
32523-WOHS S49C			ND	-	No
32523-WOHS S50A			ND	-	No
32523-WOHS S50B	536	9"x9" Floor Tile - Light Brown with Brown/White Fleck	1.2	Chrysotile	Yes
32523-WOHS S50C			Trace	Chrysotile	Yes
32523-WOHS S51A			ND	Chrysotile	Yes
32523-WOHS S51B			0.75	Chrysotile	Yes
32523-WOHS S51C	534	9"x9" Floor Tile - Dark Green with Green/White Fleck	NA	Chrysotile	Yes
32523-WOHS S51D			NA	Chrysotile	Yes
32523-WOHS S51E			NA	Chrysotile	Yes
32523-WOHS S51F			NA	Chrysotile	Yes
32523-WOHS S51G	534	2' x 4' Ceiling Tile - Dense Small Fissure Random Pinhole	ND	-	No
32523-WOHS S51H			ND	-	No
32523-WOHS S51I			ND	-	No
32523-WOHS S51J			ND	-	No
32523-WOHS S51K	Office (Near 534)	9"x9" Floor Tile - Grey/Tan with White Streaks	1.4	Chrysotile	Yes
32523-WOHS S51L			NA	Chrysotile	Yes
32523-WOHS S51M			NA	Chrysotile	Yes
32523-WOHS S51N			NA	Chrysotile	Yes

Table 3 - Sample Summary Table - Waterloo Oxford District Secondary School

TABLE 3: BULK ASBESTOS SAMPLING SUMMARY					
Sample #	WRDSB Fixed Reference Number	Material Description	Asbestos Content (%)	Fibre Type	Is Material ACM
32523-WOHS S52A	527	9"x9" Floor Tile - Dark Grey/Brown with Brown and White Fleck	1.2	Chrysotile	Yes
32523-WOHS S52B			NA	Chrysotile	Yes
32523-WOHS S52C			NA	Chrysotile	Yes
32523-WOHS S53A	530	12"x12" Floor Tile - Brown with White/Brown Spots	ND	-	No
32523-WOHS S53B			ND	-	No
32523-WOHS S53C			ND	-	No
32523-WOHS S54A	823	2' x 4' Ceiling Tile - Textured Pinhole	ND	-	No
32523-WOHS S54B			ND	-	No
32523-WOHS S54C			ND	-	No
32523-WOHS S55A	526	9"x9" Floor Tile - Red/Brown with White/Brown Streaks	1.4	Chrysotile	Yes
32523-WOHS S55B			NA	Chrysotile	Yes
32523-WOHS S55C			NA	Chrysotile	Yes
32523-WOHS S56A	524	9"x9" Floor Tile - Olive/Green/Grey with White Streaks	Layer 1: 0.75 Layer 2: ND	Chrysotile -	Yes No
32523-WOHS S56B			Layer 1: NA Layer 2: ND	Chrysotile -	Yes No
32523-WOHS S56C			Layer 1: NA Layer 2: ND	Chrysotile -	Yes No
32523-WOHS S57A	Girl's Washroom (Near 522)	12"x12" Floor Tile - Beige with Beige Fleck	ND	-	No
32523-WOHS S57B			ND	-	No
32523-WOHS S57C			ND	-	No
32523-WOHS S58A	Custodial (Near 522)	12"x12" Floor Tile - Grey with Grey/White Spots	Layer 1: ND	-	No
32523-WOHS S58B			Layer 1: ND	-	No
32523-WOHS S58C			Layer 2: 1.2	Chrysotile	Yes
32523-WOHS S59A	Hall Near Fan Room	9"x9" Floor Tile - Grey with White/Grey Streaks	Layer 1: ND	-	No
32523-WOHS S59B			1.5	Chrysotile	Yes
32523-WOHS S59C			NA	Chrysotile	Yes
32523-WOHS S60A	Mechanical Room	Plaster - Grey	NA	Chrysotile	Yes
32523-WOHS S60B			ND	-	No
32523-WOHS S60C			ND	-	No
32523-WOHS S61A	Duct Space	Drywall - Joint Compound	ND	-	No
32523-WOHS S61B			1.3	Chrysotile	Yes
32523-WOHS S61C			NA	Chrysotile	Yes
32523-WOHS S62A	Duct Space	Ceiling Finish - Fire Spray/Texture Coat Old Exterior	NA	Chrysotile	Yes
32523-WOHS S62B			ND	-	No
32523-WOHS S62C			ND	-	No
32523-WOHS S63A	Weight Room	Drywall - Joint Compound	ND	-	No
32523-WOHS S63B			ND	-	No
32523-WOHS S63C			ND	-	No
32523-WOHS S64A	Hallways Between Gyms	Plaster - White/Grey	ND	-	No
32523-WOHS S64B			ND	-	No
32523-WOHS S64C			ND	-	No
32523-WOHS S64D	808	2' x 4' Ceiling Tile - Thick Fissure	ND	-	No
32523-WOHS S64E			ND	-	No
32523-WOHS S65A			ND	-	No
32523-WOHS S65B	Phys-Ed Office	2' x 4' Ceiling Tile - Thick Fissure	ND	-	No
32523-WOHS S65C			ND	-	No
32523-WOHS S66A			ND	-	No
32523-WOHS S66B	808	12"x12" Floor Tile - Black with Grey/White Streaks	ND	-	No
32523-WOHS S66C			ND	-	No
32523-WOHS S67A			ND	-	No
32523-WOHS S67B	808	12"x12" Floor Tile - Grey with Grey/White Streaks	ND	-	No
32523-WOHS S67C			ND	-	No
32523-WOHS S68A			ND	-	No
32523-WOHS S68B	Tuck Shop	9"x9" Floor Tile - Dark Grey with White Streaks	Layer 1: 1.3 Layer 2: 3.5	Chrysotile Chrysotile	Yes Yes
32523-WOHS S68C			Layer 1: NA Layer 2: NA	Chrysotile Chrysotile	Yes Yes
32523-WOHS S69A	Boiler Room	Pipe Insulation - Boiler Breechings	5	Amosite	Yes
32523-WOHS S69B			65	Chrysotile	Yes
32523-WOHS S69C			NA	Amosite	Yes
32523-WOHS S70A	Boiler Room	Pipe Insulation - Mag Block	NA	Chrysotile	Yes
32523-WOHS S70B			85	Amosite	Yes
32523-WOHS S70C			NA	Amosite	Yes

Table 3 - Sample Summary Table - Waterloo Oxford District Secondary School

TABLE 3: BULK ASBESTOS SAMPLING SUMMARY					
Sample #	WRDSB Fixed Reference Number	Material Description	Asbestos Content (%)	Fibre Type	Is Material ACM
32523-WOHS S71A	801	Insulation - Fire Spray Beams and Columns	3.8	Chrysotile	Yes
32523-WOHS S71B			NA	Chrysotile	Yes
32523-WOHS S71C			NA	Chrysotile	Yes
32523-WOHS S72A	801	Plaster - White/Grey	ND	-	No
32523-WOHS S72B			ND	-	No
32523-WOHS S72C			ND	-	No
32523-WOHS S72D	125		ND	-	No
32523-WOHS S72E			ND	-	No
32523-WOHS S73A	CU Lunch Room	Drywall - Joint Compound	ND	-	No
32523-WOHS S73B			ND	-	No
32523-WOHS S73C			ND	-	No
32523-WOHS S74A	Men's Washroom	Vinyl Sheet Flooring - Beige with Pebble	10	Chrysotile	Yes
32523-WOHS S74B			NA	Chrysotile	Yes
32523-WOHS S74C			NA	Chrysotile	Yes
32523-WOHS S75A	127	9"x9" Floor Tile - Beige with Brown/White Fleck	1.5	Chrysotile	Yes
32523-WOHS S75B			NA	Chrysotile	Yes
32523-WOHS S75C			NA	Chrysotile	Yes
32523-WOHS S76A	125	9"x9" Floor Tile - Green with Faded Streak	1.4	Chrysotile	Yes
32523-WOHS S76B			NA	Chrysotile	Yes
32523-WOHS S76C			NA	Chrysotile	Yes
32523-WOHS S77A	208	1' x 1' Ceiling Tile - Large and Small Pinhole	ND	-	No
32523-WOHS S77B	206		ND	-	No
32523-WOHS S78A	208	2' x 4' Ceiling Tile - Short Fissure Random Pinhole	ND	-	No
32523-WOHS S78B	206		ND	-	No
32523-WOHS S79A	208	Insulation - Paper Backing	ND	-	No
32523-WOHS S79B			ND	-	No
32523-WOHS S79C			ND	-	No
32523-WOHS S80A	208	12"x12" Floor Tile - Green	ND	-	No
32523-WOHS S80B			ND	-	No
32523-WOHS S80C			ND	-	No
32523-WOHS S81A	208	Drywall - Joint Compound	ND	-	No
32523-WOHS S81B	Work Room (Between 202 and 204)		ND	-	No
32523-WOHS S81C	207		Drywall - Joint Compound	1.0	Chrysotile
32523-WOHS S81D	205	NA		Chrysotile	Yes
32523-WOHS S81E	205	NA		Chrysotile	Yes
32523-WOHS S81F	802	Drywall - Joint Compound	NA	-	No
32523-WOHS S81G	Library		NA	-	No
32523-WOHS S82A	206	Plaster - White/Grey	Layer 1: NA Layer 2: NA	-	No
32523-WOHS S82B	204		Layer 1: NA Layer 2: NA	-	No
32523-WOHS S82C	207A		Layer 1: NA Layer 2: NA	-	No
32523-WOHS S82D	207		Layer 1: NA Layer 2: NA	-	No
32523-WOHS S82E	207A		Layer 1: NA Layer 2: NA	-	No
32523-WOHS S82F	802		Layer 1: NA Layer 2: NA	-	No
32523-WOHS S82G	302/303		Layer 1: NA Layer 2: NA	-	No
32523-WOHS S83A	202		1' x 1' Ceiling Tile - Wide Fissure Random Pinhole	ND	-
32523-WOHS S83B		ND		-	No
32523-WOHS S84A	202	12"x12" Floor Tile - Taupe	2.2	Chrysotile	Yes
32523-WOHS S84B			NA	Chrysotile	Yes
32523-WOHS S84C			NA	Chrysotile	Yes
32523-WOHS S85A	Work Room (Between 204 and 204)	2' x 4' Ceiling Tile - Long Fissure Random Pinhole	ND	-	No
32523-WOHS S85B			ND	-	No
32523-WOHS S85C			ND	-	No
32523-WOHS S86A	Science Office (Between 204 and 204)	2' x 4' Ceiling Tile - Random Fissure Random Pinhole	ND	-	No
32523-WOHS S86B			ND	-	No
32523-WOHS S86C			ND	-	No
32523-WOHS S87A	207	1' x 1' Ceiling Tile - Crater with Dots	ND	-	No
32523-WOHS S87B			ND	-	No
32523-WOHS S87C			ND	-	No

Table 3 - Sample Summary Table - Waterloo Oxford District Secondary School

TABLE 3: BULK ASBESTOS SAMPLING SUMMARY					
Sample #	WRDSB Fixed Reference Number	Material Description	Asbestos Content (%)	Fibre Type	Is Material ACM
32523-WOHS S88A	207	12"x12" Floor Tile - Grey/Green	Layer 1: 2.7	Chrysotile	Yes
32523-WOHS S88B			Layer 1: NA	Chrysotile	Yes
32523-WOHS S88C			Layer 2: 0.75%	Chrysotile	Yes
			Layer 1: NA	Chrysotile	Yes
32523-WOHS S89A	201	9x9 Vinyl Floor Tile - Grey with Black	Layer 2: NA	Chrysotile	Yes
32523-WOHS S89B			2.4	Chrysotile	Yes
32523-WOHS S89C			NA	Chrysotile	Yes
32523-WOHS S90A			NA	Chrysotile	Yes
32523-WOHS S90B	Staff Room	12x12 Vinyl Floor Tile - Grey Oatmeal	ND	-	No
32523-WOHS S90C			ND	-	No
32523-WOHS S91A			ND	-	No
32523-WOHS S91B	Health Hallway	12x12 Vinyl Floor Tile - Grey with Spots	ND	-	No
32523-WOHS S91C			ND	-	No
32523-WOHS S92A			ND	-	No
32523-WOHS S92B	Library Hallway	2x2 Ceiling Tile - Short Fissure Random Pinhole	ND	-	No
32523-WOHS S92C			ND	-	No
32523-WOHS S93A			ND	-	No
32523-WOHS S93B	302	2x2 Ceiling Tile - Meal Worm	ND	-	No
32523-WOHS S93C			ND	-	No
32523-WOHS S94A			ND	-	No
32523-WOHS S94B	302	12x12 Vinyl Floor Tile - Cream with Brown	ND	-	No
32523-WOHS S94C			ND	-	No
32523-WOHS S95A			ND	-	No
32523-WOHS S95B	PED	12x12 Vinyl Floor Tile - Brown Oatmeal	Layer 1: 0.75	Chrysotile	Yes
			Layer 2: ND	-	No
			Layer 1: NA	Chrysotile	Yes
			Layer 2: ND	-	No
32523-WOHS S95C	Conference Room	9x9 Vinyl Floor Tile - Taupe with Spots	Layer 1: NA	Chrysotile	Yes
Layer 2: ND			-	No	
32523-WOHS S96A			ND	Chrysotile	Yes
32523-WOHS S96B			1.5	Chrysotile	Yes
32523-WOHS S96C	Exterior	Ceiling Finish - Exterior Texture Coat	NA	Chrysotile	Yes
32523-WOHS S97A			ND	-	No
32523-WOHS S97B			ND	-	No
32523-WOHS S97C			ND	-	No
32523-WOHS S98A	-	Ceiling Finish - Texture Coat	ND	-	No
32523-WOHS S98B			ND	-	No
32523-WOHS S98C			ND	-	No
Additional Sampling (August 2010)					
34152-200-S01A	Corridor (Stairwell 902)	Drywall Skim Coat	ND	-	No
34152-200-S01B			ND	-	No
34152-200-S01C			ND	-	No
34152-200-S02A	Adjacent to Teacher Common Room	Firespray Overspray - On Ducts	1	Actinolite	Yes
34152-200-S02B			15	Chrysotile	Yes
			NA	Actinolite	Yes
34152-200-S02C			NA	Chrysotile	Yes
34152-200-S03A	Corridor Adjacent to Room 502	Drywall Glue/Puddy	Actinolite	Chrysotile	Yes
34152-200-S03B			ND	-	No
34152-200-S03C			ND	-	No
34152-200-S04A			ND	-	No
34152-200-S04B	Boiler Room	Plaster	ND	-	No
34152-200-S04C			ND	-	No
34152-200-S05A			ND	-	No
34152-200-S05B			ND	-	No
34152-200-S05C	Exterior (Stairwell 909)	Caulking - Grey	ND	-	No
34152-200-S06A			ND	-	No
34152-200-S06B			ND	-	No
34152-200-S06C			ND	-	No
Additional Sampling (November 2010)					
34152-200-S01A	-	Vermiculite - Insulation	ND	-	No
34152-200-S01B	-		ND	-	No
34152-200-S01C	-		ND	-	No
34152-200-S01A-C	-	Vermiculite	Chatfield Analysis - ND	-	No

Table 3 - Sample Summary Table - Waterloo Oxford District Secondary School

TABLE 3: BULK ASBESTOS SAMPLING SUMMARY					
Sample #	WRDSB Fixed Reference Number	Material Description	Asbestos Content (%)	Fibre Type	Is Material ACM
2011 Asbestos Audit Update					
BR-LC- Plaster-S01a	Boiler Room	Lower Ceiling Plaster	ND	-	No
BR-LC- Plaster-S01b			ND	-	No
BR-LC- Plaster-S01c			ND	-	No
BR-UC- Plaster-S02a	Boiler Room	Upper Ceiling Plaster	ND	-	No
BR-UC- Plaster-S02b			ND	-	No
BR-UC- Plaster-S02c			ND	-	No
Additional Sampling (2013)					
WODSS –S01A	Collected by WRDSB	2'x2' Ceiling Tile	ND	-	No
WODSS –S01B			ND	-	No
WODSS –S01C			ND	-	No
Additional Sampling (July 11, 2016)					
S01A	-	Texture Coat on Canopy	ND	-	No
S01B	-	Texture Coat on Canopy	ND	-	No
S01C	-	Texture Coat on Canopy	ND	-	No
Additional Sampling (November 3, 2017)					
S01A	535	1'x1' Medium Pinhole Ceiling Tiles	ND	-	No
S01B	535	1'x1' Medium Pinhole Ceiling Tiles	ND	-	No
S01C	535	1'x1' Medium Pinhole Ceiling Tiles	ND	-	No
Additional Sampling (April 9, 2018)					
S01A	811	Ceiling Tiles - Random Fissure Pattern	ND	-	No
S01B	811	Ceiling Tiles - Random Fissure Pattern	ND	-	No
S01C	811	Ceiling Tiles - Random Fissure Pattern	ND	-	No
S02A	811	Ceiling Tiles - Small Fissure Pattern	ND	-	No
S02B	811	Ceiling Tiles - Small Fissure Pattern	ND	-	No
S02C	811	Ceiling Tiles - Small Fissure Pattern	ND	-	No
2018 Asbestos Audit Update					
S01A	403B	2'x4' Small Fissure Small Pinhole Ceiling Tile	ND	-	No
S01B	403B	2'x4' Small Fissure Small Pinhole Ceiling Tile	ND	-	No
S01C	403B	2'x4' Small Fissure Small Pinhole Ceiling Tile	ND	-	No
S02A	513A	2'x4' Medium Fissure Random Pinhole Ceiling Tile	ND	-	No
S02B	513A	2'x4' Medium Fissure Random Pinhole Ceiling Tile	ND	-	No
S02C	513A	2'x4' Medium Fissure Random Pinhole Ceiling Tile	ND	-	No
S03A	512B	Plaster - 1962 Addition	ND	-	No
S03B	510	Plaster - 1962 Addition	ND	-	No
S03C	510	Plaster - 1962 Addition	ND	-	No
S04A	512C	1'x1' B/S PH Ceiling Tile - Brown Mastic	ND	-	No
S04B	512C	1'x1' B/S PH Ceiling Tile - Brown Mastic	ND	-	No
S04C	512C	1'x1' B/S PH Ceiling Tile - Brown Mastic	ND	-	No
S05A	809	2'x2' Dense Fissure Random Pinhole Ceiling Tile	5	Amosite	Yes
S05B	809	2'x2' Dense Fissure Random Pinhole Ceiling Tile	NA	Amosite	Yes
S05C	809	2'x2' Dense Fissure Random Pinhole Ceiling Tile	NA	Amosite	Yes
S06A	809	2'x2' Medium Fissure Pinhole Ceiling Tile	ND	-	No
S06B	809	2'x2' Medium Fissure Pinhole Ceiling Tile	ND	-	No
S06C	809	2'x2' Medium Fissure Pinhole Ceiling Tile	ND	-	No
S07A	305	12"x12" Teal Dense Fleck Floor Tile	ND	-	No
S07B	305	12"x12" Teal Dense Fleck Floor Tile	ND	-	No
S07C	305	12"x12" Teal Dense Fleck Floor Tile	ND	-	No
S08A	207A	1'x1' Texture Fissure Pinhole Ceiling Tile	ND	-	No
S08B	207A	1'x1' Texture Fissure Pinhole Ceiling Tile	ND	-	No
S08C	207A	1'x1' Texture Fissure Pinhole Ceiling Tile	ND	-	No
S09A	104	9"x9" Olive with White Streak Floor Tile	2	Chrysotile	Yes
S09B	104	9"x9" Olive with White Streak Floor Tile	NA	Chrysotile	Yes
S09C	104	9"x9" Olive with White Streak Floor Tile	NA	Chrysotile	Yes
S10A	400B	2'x4' Texture Pinhole Ceiling Tile	ND	-	No
S10B	400B	2'x4' Texture Pinhole Ceiling Tile	ND	-	No
S10C	400B	2'x4' Texture Pinhole Ceiling Tile	ND	-	No
S11A	122	9"x9" Olive w Black Streak Vinyl Floor Tiles	1	Chrysotile	Yes
S11B	122	9"x9" Olive w Black Streak Vinyl Floor Tiles	NA	Chrysotile	Yes
S11C	122	9"x9" Olive w Black Streak Vinyl Floor Tiles	NA	Chrysotile	Yes
S12A	522	1'x1' Large/Medium Pinhole Cellulose Ceiling Tile Brown Mastic	ND	-	No
S12B	522	1'x1' Large/Medium Pinhole Cellulose Ceiling Tile Brown Mastic	ND	-	No

Table 3 - Sample Summary Table - Waterloo Oxford District Secondary School

TABLE 3: BULK ASBESTOS SAMPLING SUMMARY

Sample #	WRDSB Fixed Reference Number	Material Description	Asbestos Content (%)	Fibre Type	Is Material ACM
S12C	522	1'x1' Large/Medium Pinhole Cellulose Ceiling Tile Brown Mastic	ND	-	No
S13A	530	1'x1' Large/Medium Pinhole Ceiling Tile	ND	-	No
S13B	530	1'x1' Large/Medium Pinhole Ceiling Tile	ND	-	No
S13C	530	1'x1' Large/Medium Pinhole Ceiling Tile	ND	-	No
2018 Asbestos Audit Update, Additional Sampling (October 5, 2018)					
S01A	518	Beige Sealant on Interior Doors (1972)	ND	-	No
S01B	518	Beige Sealant on Interior Doors (1972)	ND	-	No
S01C	518	Beige Sealant on Interior Doors (1972)	ND	-	No
S02A	518	Brown Sealant on Exterior Doors (1972)	8	Chrysotile	Yes
S02B	518	Brown Sealant on Exterior Doors (1972)	NA	Chrysotile	Yes
S02C	518	Brown Sealant on Exterior Doors (1972)	NA	Chrysotile	Yes
S03A	517	Beige Sealant on Interior Window Frames (1972)	8	Chrysotile	Yes
S03B	517	Beige Sealant on Interior Window Frames (1972)	NA	Chrysotile	Yes
S03C	517	Beige Sealant on Interior Window Frames (1972)	NA	Chrysotile	Yes
S04A	824	Beige Sealant on Interior Window Frames (1962)	1	Chrysotile	Yes
S04B	824	Beige Sealant on Interior Window Frames (1962)	NA	Chrysotile	Yes
S04C	824	Beige Sealant on Interior Window Frames (1962)	NA	Chrysotile	Yes
S05A	1009	Beige Sealant on Interior Window Frames (1966)	5	Chrysotile	Yes
S05B	1009	Beige Sealant on Interior Window Frames (1966)	NA	Chrysotile	Yes
S05C	1009	Beige Sealant on Interior Window Frames (1966)	NA	Chrysotile	Yes
2022 Additional Sampling (October 3, 2022)					
S01A	102A	Trowel Applied Fireproofing	40	Chrysotile	Yes
S01B	102A	Trowel Applied Fireproofing	NA	Chrysotile	Yes
S01C	102A	Trowel Applied Fireproofing	NA	Chrysotile	Yes

NA: Not Analyzed due to stop positive method ND: No asbestos fibres detected above the laboratory minimum detection limit

A bulk material sample containing 0.5% or more asbestos therefore establishes that material as asbestos-containing. In accordance with Table 1 of O. Reg. 278/05, a minimum number of samples for the material to be classified as non asbestos. A homogeneous material is defined by O. Reg. 278/05 "as material that is uniform in colour and texture". Homogeneous samples are identified by an alphabetical suffix to sample names to represent multiple samples of a homogeneous material. When a homogeneous material is analysed it is determined to be asbestos-containing upon the first positive detection of asbestos equal to or greater than 0.5%. Subsequent samples of the same material are therefore not analysed. Some bulk samples are comprised of multiple layers and as such will require multiple analysis. In such cases each layer is isolated at the laboratory and analysed individually to determine asbestos content. As a result the laboratory may report additional samples beyond the submitted number of samples or include multiple analyses as subsets within a sample.

Certificate of Analysis

MTE Consultants Inc. (Kitchener)

520 Bingemans Centre Dr.
Kitchener, ON N2B 3X9
Attn: Paul Semeniuk

Client PO: 34532-940

Project: 34532-940 WO-100 Series 2nd Mech

Custody:

Report Date: 13-Oct-2022

Order Date: 6-Oct-2022

Order #: 2241396

This Certificate of Analysis contains analytical data applicable to the following samples as submitted:

Paracel ID

2241396-01

2241396-02

2241396-03

Client ID

S01A - Trowel Applied Fire Proofing - Rm 120A

S01B - Trowel Applied Fire Proofing - Rm 120A

S01C - Trowel Applied Fire Proofing - Rm 120A

Approved By:



Emma Diaz

Senior Analyst

Certificate of Analysis
Client: MTE Consultants Inc. (Kitchener)

Report Date: 13-Oct-2022

Order Date: 6-Oct-2022

Client PO: 34532-940

Project Description: 34532-940 WO-100 Series 2nd Mech

Asbestos, PLM Visual Estimation **MDL - 0.5%**

Paracel ID	Sample Date	Colour	Description	Asbestos Detected	Material Identification	% Content
2241396-01	03-Oct-22	Grey	Fireproofing	Yes	Client ID: S01A - Trowel Applied Fire Proofing - Rm 120A [Z-01] Chrysotile Non-Fibers	 40 60
2241396-02	03-Oct-22	Grey	Fireproofing		Client ID: S01B - Trowel Applied Fire Proofing - Rm 120A [Z-01] not analyzed, positive stop	
2241396-03	03-Oct-22	Grey	Fireproofing		Client ID: S01C - Trowel Applied Fire Proofing - Rm 120A [Z-01] not analyzed, positive stop	

**** Analytes in bold indicate asbestos mineral content.**
Analysis Summary Table

Analysis	Method Reference/Description	Lab Location	Lab Accreditation	Analysis Date
Asbestos, PLM Visual Estimation	AppE to SubE of 40CFR Part753 and EPA/600/R-93/116	1 - Mississauga	CALA 3762	12-Oct-22

Mississauga Lab: 15 - 6800 Kitimat Rd Mississauga, Ontario, L5N 5M1

Qualifier Notes

Sample Qualifiers :

Z-01: Sample contains vermiculite.

Work Order Revisions | Comments

None

Attachment 2

Supportive Documentation

For Tender Purposes



September 24, 2012
MTE File No.: 34152-500

Ms. Daniela Budure
Environmental Officer
Waterloo Region District School Board
51 Ardelt Avenue
Kitchener, ON N2C 2R5

Dear Ms. Budure:

**Re: Results of Total Airborne Fibre Sampling at
Waterloo-Oxford District Secondary School,
1206 Snyders Road West, Cambridge, Ontario**

MTE Consultants Inc. (MTE) was retained by the Waterloo Region District School Board (WRDSB) to complete a sampling event as part of an ongoing program to assess airborne asbestos fibre concentrations in conjunction with ongoing asbestos management at Waterloo-Oxford District Secondary School (WODSS) located at 1206 Snyders Road West in Cambridge, Ontario.

BACKGROUND

The WRDSB, along with MTE, developed a strategy to manage and monitor the existing spray fireproofing within WODSS.

In September 2012, inspection services, documentation, and air monitoring programs were developed and conducted by MTE. A portion of the above mentioned monitoring program included ongoing sampling for total airborne fibre analysis by Phase Contrast Microscopy (PCM) to assess any potential risk of building occupant exposure to airborne asbestos fibres. Air sampling will continue as part of the ongoing monitoring program, and sampling will be conducted on a bi-annual basis, as requested by the WRDSB.

SCOPE OF WORK

The scope of MTE's services for this assignment was:

- Collection of three (3) air samples from selected corridors on the First floor and preparation of one (1) blank sample for fibre analysis;
- Submission of samples to an accredited laboratory for analysis of total airborne fibre by PCM;

- Interpretation of analytical results with respect to occupational worker exposure; and
- Preparation of a letter report of findings with appropriate recommendations, if required.

METHODOLOGY

In conjunction with the ongoing management program, air samples were collected by MTE from selected corridors on September 12, 2012. A total of three (3) air samples were collected and one (1) blank sample was prepared for quality control purposes. Samples were collected in accordance with The National Institute for Occupational Safety and Health (NIOSH) Method 7400 and were submitted to EMSL Canada Inc. in Mississauga, Ontario. Table 1 provides a summary of sample locations and laboratory analytical results.

EMSL is accredited through the National Voluntary Laboratory Accreditation Program (NVLAP) for airborne analysis by PCM. Laboratory certificates of analysis are provided as an attachment to this report. The sampling event was conducted after normal class hours. In order to obtain samples representative of typical conditions within the building during occupancy, the day-time operational settings of the buildings heating and ventilation system were maintained throughout the sampling event. The sampling event also started immediately following class dismissal to obtain the most accurate representation of classroom activity.

TABLE 1: SUMMARY OF AIRBORNE FIBRE CONCENTRATIONS AT SELECTED SAMPLE LOCATIONS THROUGHOUT WODSS ON SEPTEMBER 12, 2012 AS DETERMINED BY PHASE CONTRAST MICROSCOPY

Sample Name	Sample Location	Sample Air Volume Collected (L)	Analytical Results: Fibres per cubic centimetre of Air (f/cc)
CC419777	1 st Floor – Corridor 7	1800	0.002
CC419808	1 st Floor – Corridor 4	1800	<0.001
CC419788	1 st Floor – Corridor 1	1800	<0.001
CC419795	Blank	Not Applicable	Non-detect*

*No detections of fibres based on the laboratory detection limit reported for blank sample.

DISCUSSION

Airborne Fibres

One of the three air samples collected within the selected corridor sample locations reported concentrations of total airborne fibres to be above the laboratory method detection limit of 0.001 fibres per cubic centimetre of air (f/cc).

It should be noted that the analysis method does not distinguish between asbestos fibres and other fibre sources. Sample method detection limits have been rounded to the nearest significant digit. Ontario Regulation 490/09 Designated Substances prescribes an acceptable Time Weighted Average Exposure Value (TWAEV) to asbestos fibre of not more than 0.1 fibres per cubic centimetre of air (f/cc). Standard industrial hygiene practice considers a concentration greater than one half the TWAEV (0.05 f/cc) as actionable in order to control exposure and ensure worker safety. Ontario Regulation 278/05 Designated Substance – Asbestos on Construction Projects and in Buildings and Repair Operations prescribes an acceptable post asbestos removal air clearance concentration of not more than 0.01 f/cc or one tenth the TWAEV. This concentration is deemed protective of human health for workers and occupants of the building. All samples reported concentrations of total airborne fibres to be less than the clearance criteria of 0.01 f/cc. The reported concentrations do not suggest an overexposure to airborne asbestos for workers or building occupants.

CONCLUSIONS AND RECOMMENDATIONS

Based on analytical results the following conclusions are presented:

- Total airborne fibre concentrations within the sampled corridors are well below the Ontario Ministry of Labour TWAEV acceptable abatement and clearance criteria prescribed in Ontario Regulation 490/09 and 278/05 respectively;
- The reported concentrations in the air samples do not indicate workers or building occupants are at any elevated risk of over exposure to airborne asbestos fibres, under current site conditions;
- These findings should be incorporated into the building asbestos audit and Asbestos Management Program; and
- If work is required which will disturb or is likely to disturb asbestos-containing material, the work must be conducted in accordance with Ontario Regulation 278/05 by trained and certified asbestos removal contractors.

LIMITATIONS

Services performed by **MTE Consultants Inc.** (MTE) were conducted in a manner consistent with the level of care and skill ordinarily exercised by members of the Environmental Engineering & Consulting profession. No other representation expressed or implied as to the accuracy of the information, conclusions or recommendations is included or intended in this report.

This report was completed for the sole use of MTE and Waterloo Region District School Board. It was completed in accordance with the Scope of Work. As such, this report may not deal with all issues potentially applicable to the site and may omit issues, which are or may be of interest to the reader. MTE makes no representation that the present report has dealt with all-important environmental features, except as provided in the Scope of Work. All findings and conclusions presented in this report are based on site conditions, as they existed during the time period of the investigation. This report is not intended to be exhaustive in scope or to imply a risk-free facility.

Some areas could not be investigated due to non-destructive, non-invasive, inspection restrictions or prohibited access. Although the presence of asbestos-containing materials (ACM) has been anticipated in these areas where reasonable, the accuracy of such information must be confirmed before any potential disturbance of materials which may contain asbestos. It is also possible that ACM may be visually or physically concealed by but not necessarily limited to ceilings, walls, bulkheads, floors, roof systems or other similar features or structures.

Any use which a third party makes of this report, or any reliance on, or decisions to be made based upon it, are the responsibility of such third parties. MTE accepts no responsibility for liabilities incurred by or damages, if any, suffered by any third party as a result of decisions made or actions taken, based upon this report. Others with interest in the site should undertake their own investigations and studies to determine how or if the condition affects them or their plans.

It should be recognized that the passage of time may affect the views, conclusions and recommendations (if any) provided in this report because environmental conditions of a property can change. Should additional or new information become available, MTE recommends that it be brought to our attention in order that we may re-assess the contents of this report.

Sincerely,

MTE CONSULTANTS INC.



For
Greg Eller, BA, C.Tech. LEED AP (BD+C)
Project Manager
geller@mte85.com



Paul Semeniuk, B.E.S.
Building Health Sciences Technologist
psemeniuk@mte85.com

GSE:ksr

Attach.

M:\34152\500\Report\September 2012\34152-500 - Air Sampling Report - Waterloo-Oxford D.S.S. - September-24-2012.doc

For Tender Purposes

**EMSL Canada Inc.**

10 Falconer Drive, Unit #3, Mississauga, ON L5N 3L8

Phone/Fax: 289-997-4602 / (289) 997-4607

<http://www.emsl.com>torontolab@emsl.com

EMSL Canada Or 551204186

CustomerID: 55MCFE78

CustomerPO: 34152-500

ProjectID:

Attn: **Paul Semeniuk**
MTE Consultants, Inc.
520 Bingemans Centre Drive

Kitchener, ON N2B 3X9

Project: 1206 SNYDERS ROAD WEST-34152-500

Phone: (519) 743-6500
Fax: (519) 743-6513
Received: 09/14/12 11:06 AM
Analysis Date: 9/21/2012
Collected: 9/12/2012

Test Report: Fiber Count by Phase Contrast Microscopy (PCM), NIOSH 7400 Method,
Revision 3, Issue 2, 8/15/94

Sample	Location	Sample Date	Volume (liters)	Fibers	Fields	LOD (fib/cc)	Fibers/ mm ²	Fibers/ cc	Notes
CC419777	CORRIDOR 7	9/12/2012	1800.00	7.5	100	0.001	9.55	0.002	
551204186-0001									
CC419808	CORRIDOR 4	9/12/2012	1800.00	<5.5	100	0.001	<7.0	<0.001	
551204186-0002									
CC419788	CORRIDOR 1	9/12/2012	1800.00	<5.5	100	0.001	<7.0	<0.001	
551204186-0003									
CC419795	BLANK			<5.5	100		<7.0		Field Blank
551204186-0004									

The results reported have been blank corrected as applicable.

Analyst(s)

Kevin Pang (4)

Kevin Pang
or other approved signatory

Limit of detection is 7 fibers/mm². Intra-laboratory Sr values: 5-20 fibers = 0.32, 21-50 fibers = 0.24, 51-100 fibers = 0.17. Inter-laboratory Sr values (Average of EMSL round robin data) = 0.29. The laboratory is not responsible for data reported in fibers/cc, which is dependent on volume collected by non-laboratory personnel. Results have been blank corrected as applicable. EMSL maintains liability limited to cost of analysis. This report relates only to the samples reported above and may not be reproduced, except in full, without written approval by EMSL. EMSL bears not responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. Samples received in good condition unless otherwise noted.

Samples analyzed by EMSL Canada Inc. Mississauga, ON

Initial report from 09/21/2012 09:15:39



April 10, 2013
MTE File No.: 34152-500

Ms. Daniela Budure
Environmental Officer
Waterloo Region District School Board
51 Ardelt Avenue
Kitchener, ON N2C 2R5

Dear Ms. Budure:

**Re: Results of Total Airborne Fibre Sampling at
Waterloo-Oxford District Secondary School,
1206 Snyders Road West, Cambridge, Ontario**

MTE Consultants Inc. (MTE) was retained by the Waterloo Region District School Board (WRDSB) to complete a sampling event as part of an ongoing program to assess airborne asbestos fibre concentrations in conjunction with ongoing asbestos management at Waterloo-Oxford District Secondary School (W-ODSS) located at 1206 Snyders Road West in Cambridge, Ontario.

BACKGROUND

The WRDSB, along with MTE, developed a strategy to manage and monitor the existing spray fireproofing within W-ODSS.

In September 2012, inspection services, documentation, and air monitoring programs were developed and conducted by MTE. A portion of the above-mentioned monitoring program included ongoing sampling for total airborne fibre analysis by Phase Contrast Microscopy (PCM) to assess any potential risk to building occupants with regards to exposure to airborne asbestos fibres. Air sampling will continue as part of the ongoing monitoring program, and sampling will be conducted on a bi-annual basis, as requested by the WRDSB.

As part of the ongoing monitoring program air sampling was conducted between September, 2012 and March 2013. Analytical results from the previous sampling events are documented in MTE's previous reports and are listed in an attachment to this report.

This report should be read in conjunction with previous reports related to airborne fibre sampling at the school.

Sampling is conducted on a bi-annual basis, as requested by the WRDSB.

SCOPE OF WORK

The scope of MTE's services for this assignment was:

- Collection of three (3) air samples from selected corridors on the first and second floors;
- Analysis of total airborne fibre by Phase Contrast Microscopy following the National Institute of Occupational Safety and Health US (NIOSH) Method 7400;
- Interpretation of analytical results with respect to occupational worker exposure; and
- Preparation of a letter report of findings with appropriate recommendations, if required.

METHODOLOGY

In conjunction with the ongoing management program, air samples were collected by MTE from selected classrooms on March 14, 2013. A total of three (3) air samples were collected. Samples were collected in accordance with The National Institute for Occupational Safety and Health (NIOSH) Method 7400 and were analyzed by MTE. MTE participates and maintains proficient standing in the Canadian Association for Laboratory Accreditation (CALA) proficiency testing in asbestos and other fibres in air by Phase Contrast Microscopy Analysis under Membership number 3827. Table 1 provides a summary of sample locations and laboratory analytical results.

TABLE 1: SUMMARY OF AIRBORNE FIBRE CONCENTRATIONS AT SELECTED SAMPLE LOCATIONS THROUGHOUT WODSS ON MARCH 14, 2013 AS DETERMINED BY PHASE CONTRAST MICROSCOPY

Sample Name	Sample Location	Sample Air Volume Collected (L)	Analytical Results: Fibres per cubic centimetre of Air (f/cc)
BW828436	1 st Floor – Transportation Technology 510	1800	<0.011
BW828198	1 st Floor – Department Head Offices 101	1800	<0.011
BW828452	2 nd Floor – Classroom 527	1800	<0.011

DISCUSSION

Airborne Fibres

All three air samples collected within the selected corridor sample locations reported concentrations of total airborne fibres to be below the reporting limit of 0.011 fibres per cubic centimetre of air (f/cc).

It should be noted that the analysis method does not distinguish between asbestos fibres and other fibre sources. Sample method detection limits have been rounded to the nearest significant digit. Ontario Regulation 490/09 Designated Substances prescribes an acceptable Time Weighted Average Exposure Value (TWAEV) to asbestos fibre of not more than 0.1 fibres per cubic centimetre of air (f/cc). Standard industrial hygiene practice considers a concentration greater than one half the TWAEV (0.05 f/cc) as actionable in order to control exposure and ensure worker safety. Ontario Regulation 278/05 Designated Substance – Asbestos on Construction Projects and in Buildings and Repair Operations prescribes an acceptable post asbestos removal air clearance concentration of not more than 0.01 f/cc or one tenth the TWAEV. This concentration is deemed protective of human health for workers and occupants of the building. All samples reported concentrations of total airborne fibres to be less than the clearance criteria of 0.01 f/cc. The reported concentrations do not suggest an overexposure to airborne asbestos for workers or building occupants.

CONCLUSIONS AND RECOMMENDATIONS

Based on analytical results the following conclusions are presented:

- Total airborne fibre concentrations within the sampled corridors are well below the Ontario Ministry of Labour TWAEV acceptable abatement and clearance criteria prescribed in Ontario Regulation 490/09 and 278/05 respectively;
- The reported concentrations in the air samples do not indicate workers or building occupants are at any elevated risk of over exposure to airborne asbestos fibres, under current site conditions;
- These findings should be incorporated into the building asbestos audit and Asbestos Management Program; and
- If work is required which will disturb or is likely to disturb asbestos-containing material, the work must be conducted in accordance with Ontario Regulation 278/05 by trained and certified asbestos removal contractors.

LIMITATIONS

Services performed by **MTE Consultants Inc.** (MTE) were conducted in a manner consistent with the level of care and skill ordinarily exercised by members of the Environmental Engineering & Consulting profession. No other representation expressed or implied as to the accuracy of the information, conclusions or recommendations is included or intended in this report.

This report was completed for the sole use of MTE and Waterloo Region District School Board. It was completed in accordance with the Scope of Work. As such, this report may not deal with all issues potentially applicable to the site and may omit issues, which are or may be of interest to the reader. MTE makes no representation that the present report has dealt with all-important environmental features, except as provided in the Scope of Work. All findings and conclusions presented in this report are based on site conditions, as they existed during the time period of the investigation. This report is not intended to be exhaustive in scope or to imply a risk-free facility.


Some areas could not be investigated due to non-destructive, non-invasive, inspection restrictions or prohibited access. Although the presence of asbestos-containing materials (ACM) has been anticipated in these areas where reasonable, the accuracy of such information must be confirmed before any potential disturbance of materials which may contain asbestos. It is also possible that ACM may be visually or physically concealed by but not necessarily limited to ceilings, walls, bulkheads, floors, roof systems or other similar features or structures.

Any use which a third party makes of this report, or any reliance on, or decisions to be made based upon it, are the responsibility of such third parties. MTE accepts no responsibility for liabilities incurred by or damages, if any, suffered by any third party as a result of decisions made or actions taken, based upon this report. Others with interest in the site should undertake their own investigations and studies to determine how or if the condition affects them or their plans.


It should be recognized that the passage of time may affect the views, conclusions and recommendations (if any) provided in this report because environmental conditions of a property can change. Should additional or new information become available, MTE recommends that it be brought to our attention in order that we may re-assess the contents of this report.

Sincerely,

MTE CONSULTANTS INC.



Greg Eiler, BA, C.Tech. LEED AP (BD+C)
Project Manager
geller@mte85.com



Paul Semeniuk, B.E.S.
Building Health Sciences Technologist
psemeniuk@mte85.com

GSE:plw

Attach:

M:\34152\500\PDFs\March 2013\34152-500 - Air Sampling Report - Waterloo-Oxford D.S.S. - April-10-13.doc

For Tender Purposes

List of Previous MTE Reports – Waterloo-Oxford District Secondary School – Airborne Fibre Sampling: MTE #: 34152-500

- “*Results of Total Airborne Fibre Sampling at Waterloo-Oxford District Secondary School, 1206 Snyders Road West, Cambridge, Ontario*”, dated September 24, 2012. MTE #: 34152-500.

For Tender Purposes

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS REPORT

Samples were analyzed using a Zeiss Axio Star Plus or Nikon Eclipse E100 Phase Contrast Microscope in accordance with NIOSH method 7400 "Asbestos and Other Fibres by PCM". The results of this report apply only to the materials tested.

CLIENT INFORMATION

Client Name: **WRDSB**

Project No: **34152-500**

Client Address: 51 Ardelt Avenue, Kitchener, ON N2C 2R5

Site Address: 1206 Snyders Rd W Baden, ON N3A 1A4

SAMPLING INFORMATION

Sampled by: PXS

Sampling date: Mar-14-13

Analyzed by: MJM

Analysis date: Mar-26-13

Analyst Signature: 

Manager's Signature: 

SAMPLE INFORMATION

Sample #: 1552

Cassette Barcode Number: BW828436

Sample ID: **WODSS-34152-500-AS1**

Fibres/field: 0.105

Flow Rate (L/min): 15.00

Cassette Size (mm²): 385

Duration (min): 120

Field Size: 0.00785

Volume (L): 1800

R.L. ≤ **0.011** (f/cc)

Notes:

- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air

MTE Consultants Inc. participates and maintains proficient standing in the Canadian Association for Laboratory Accreditation Inc. (CALA) Asbestos Proficiency Testing for Asbestos and Other Fibres in air by Phase Contrast Microscopy (PCM) analysis under Membership Number 3827.

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS REPORT

Samples were analyzed using a Zeiss Axio Star Plus or Nikon Eclipse E100 Phase Contrast Microscope in accordance with NIOSH method 7400 "Asbestos and Other Fibres by PCM". The results of this report apply only to the materials tested.

CLIENT INFORMATION

Client Name: **WRDSB**

Project No: **34152-500**

Client Address: 51 Ardelt Avenue, Kitchener, ON N2C 2R5

Site Address: 1206 Snyders Rd W Baden, ON N3A 1A4

SAMPLING INFORMATION


Sampled by: PXS

Sampling date: Mar-14-13

Analyzed by: MJM

Analysis date: Mar-26-13

Analyst Signature: 

Manager's Signature: 

SAMPLE INFORMATION

Sample #: 1553

Cassette Barcode Number: BW828198

Sample ID: **WODSS-34152-500-AS2**

Fibres/field: 0.180

Flow Rate (L/min): 15.00

Cassette Size (mm²): 385

Duration (min): 120

Field Size: 0.00785

Volume (L): 1800

R.L. ≤ **0.011** (f/cc)

Notes:

- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS REPORT

Samples were analyzed using a Zeiss Axio Star Plus or Nikon Eclipse E100 Phase Contrast Microscope in accordance with NIOSH method 7400 "Asbestos and Other Fibres by PCM". The results of this report apply only to the materials tested.

CLIENT INFORMATION

Client Name: **WRDSB**

Project No: **34152-500**

Client Address: 51 Ardel Avenue, Kitchener, ON N2C 2R5

Site Address: 1206 Snyders Rd W Baden, ON N3A 1A4

SAMPLING INFORMATION

Sampled by: PXS

Sampling date: Mar-14-13

Analyzed by: MJM

Analysis date: Mar-26-13

Analyst Signature: 

Manager's Signature: 

SAMPLE INFORMATION

Sample #: 1554

Cassette Barcode Number: BW828452

Sample ID: **WODSS-34152-500-AS3**

Fibres/field: 0.055

Flow Rate (L/min): 15.00

Cassette Size (mm²): 385

Duration (min): 120

Field Size: 0.00785

Volume (L): 1800

R.L. ≤ **0.011** (f/cc)

Notes:

- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air



September 2, 2016
MTE File No.: C34152-900

Ms. Daniela Budure
Environmental Officer
Waterloo Region District School Board
51 Ardelt Avenue
Kitchener, ON N2C 2R5

Dear Ms. Budure:

**Re: Results of Total Airborne Fibre Sampling at
Waterloo-Oxford District Secondary School,
1206 Snyders Road West, Cambridge, Ontario**

MTE Consultants Inc. (MTE) was retained by the Waterloo Region District School Board (WRDSB) to complete a sampling event as part of an ongoing program to assess airborne asbestos fibre concentrations in conjunction with ongoing asbestos management at Waterloo-Oxford District Secondary School (WODSS) located at 1206 Snyders Road West in Cambridge, Ontario.

BACKGROUND

The WRDSB, along with MTE, developed a strategy to manage and monitor the existing spray fireproofing within WODSS.

In September 2012, inspection services, documentation, and air monitoring programs were developed and conducted by MTE. A portion of the above mentioned monitoring program included ongoing sampling for total airborne fibre analysis by Phase Contrast Microscopy (PCM) to assess any potential risk of building occupant exposure to airborne asbestos fibres. Air sampling will continue as part of the ongoing monitoring program, and sampling will be conducted on a bi-annual basis, as requested by the WRDSB.

As part of the ongoing monitoring program air sampling was conducted between September, 2012 and March 2013. Analytical results from the previous sampling events are documented in MTE's previous reports.

This report should be read in conjunction with previous reports related to airborne fibre sampling at the school.

Sampling is conducted on an annual basis, as requested by the WRDSB.

SCOPE OF WORK

The scope of MTE's services for this assignment was:

- Collection of three (3) air samples from selected corridors on the first and second floors;
- Analysis of total airborne fibre by Phase Contrast Microscopy following the National Institute of Occupational Safety and Health US (NIOSH) Method 7400;
- Interpretation of analytical results with respect to occupational worker exposure; and
- Preparation of a letter report of findings with appropriate recommendations, if required.

METHODOLOGY

In conjunction with the ongoing management program, air samples were collected by MTE from selected locations on September 1, 2016. A total of three (3) air samples were collected. Samples were collected in accordance with The National Institute for Occupational Safety and Health (NIOSH) Method 7400 and were analyzed by MTE. MTE participates and maintains proficient standing in the Canadian Association for Laboratory Accreditation (CALA) proficiency testing in asbestos and other fibres in air by Phase Contrast Microscopy Analysis under Membership number 3827. Table 1 provides a summary of sample locations and laboratory analytical results.

TABLE 1: SUMMARY OF AIRBORNE FIBRE CONCENTRATIONS AT SELECTED SAMPLE LOCATIONS THROUGHOUT WODSS ON SEPTEMBER 1, 2016 AS DETERMINED BY PHASE CONTRAST MICROSCOPY

Sample Name	Sample Location	Sample Air Volume Collected (L)	Analytical Results: Fibres per cubic centimetre of Air (f/cc)
CU990730	1 st Floor Corridor 803 (outside 507)	2700	<0.007
CU990520	1 st Floor Science Classroom 102	2700	<0.007
CL993480	2 nd Floor Corridor 821 (100 Series)	2700	<0.007

DISCUSSION

Airborne Fibres

All three air samples collected within the selected corridor sample locations reported concentrations of total airborne fibres to be below the reporting limit of 0.007 fibres per cubic centimetre of air (f/cc).

It should be noted that the analysis method does not distinguish between asbestos fibres and other fibre sources. Sample method detection limits have been rounded to the nearest significant digit. Ontario Regulation 490/09 Designated Substances prescribes an acceptable Time Weighted Average Exposure Value (TWAEV) to asbestos fibre of not more than 0.1 fibres per cubic centimetre of air (f/cc). Standard industrial hygiene practice considers a concentration greater than one half the TWAEV (0.05 f/cc) as actionable in order to control exposure and ensure worker safety. Ontario Regulation 278/05 Designated Substance – Asbestos on Construction Projects and in Buildings and Repair Operations prescribes an acceptable post asbestos removal air clearance concentration of not more than 0.01 f/cc or one tenth the TWAEV. This concentration is deemed protective of human health for workers and occupants of the building. All samples reported concentrations of total airborne fibres to be less than the clearance criteria of 0.01 f/cc. The reported concentrations do not suggest an overexposure to airborne asbestos for workers or building occupants.

CONCLUSIONS AND RECOMMENDATIONS

Based on analytical results the following conclusions are presented:

- Total airborne fibre concentrations within the sampled locations are well below the Ontario Ministry of Labour TWAEV acceptable abatement and clearance criteria prescribed in Ontario Regulation 490/09 and 278/05 respectively;
- The reported concentrations in the air samples do not indicate workers or building occupants are at any elevated risk of over-exposure to airborne asbestos fibres, under current site conditions;
- These findings should be incorporated into the building asbestos audit and Asbestos Management Program; and
- If work is required which will disturb or is likely to disturb asbestos-containing material, the work must be conducted in accordance with Ontario Regulation 278/05 by trained and certified asbestos removal contractors.



LIMITATIONS

Services performed by **MTE Consultants Inc.** (MTE) were conducted in a manner consistent with the level of care and skill ordinarily exercised by members of the Environmental Engineering & Consulting profession. No other representation expressed or implied as to the accuracy of the information, conclusions or recommendations is included or intended in this report.

This report was completed for the sole use of MTE and Waterloo Region District School Board. It was completed in accordance with the Scope of Work. As such, this report may not deal with all issues potentially applicable to the site and may omit issues, which are or may be of interest to the reader. MTE makes no representation that the present report has dealt with all-important environmental features, except as provided in the Scope of Work. All findings and conclusions presented in this report are based on site conditions, as they existed during the time period of the investigation. This report is not intended to be exhaustive in scope or to imply a risk-free facility.

Some areas could not be investigated due to non-destructive, non-invasive, inspection restrictions or prohibited access. Although the presence of asbestos-containing materials (ACM) has been anticipated in these areas where reasonable, the accuracy of such information must be confirmed before any potential disturbance of materials which may contain asbestos. It is also possible that ACM may be visually or physically concealed by but not necessarily limited to ceilings, walls, bulkheads, floors, roof systems or other similar features or structures.

Any use which a third party makes of this report, or any reliance on, or decisions to be made based upon it, are the responsibility of such third parties. MTE accepts no responsibility for liabilities incurred by or damages, if any, suffered by any third party as a result of decisions made or actions taken, based upon this report. Others with interest in the site should undertake their own investigations and studies to determine how or if the condition affects them or their plans.

It should be recognized that the passage of time may affect the views, conclusions and recommendations (if any) provided in this report because environmental conditions of a property can change. Should additional or new information become available, MTE recommends that it be brought to our attention in order that we may re-assess the contents of this report.

Sincerely,

MTE CONSULTANTS INC.

A handwritten signature in black ink, appearing to read "Martin Mielke", is positioned above the printed name.

Martin Mielke, B.Sc, CRSP
Technical Advisor
mmielke@mte85.com

MJM:mjm

Attach:

M:\34152\104 - Phase 3\Bi-Annual Air Sampling\34152-104 - Air Sampling Report - Waterloo-Oxford D.S.S. - August 2015.doc



ATTACHMENTS

For Tender Purposes

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS WORKSHEET

Client: WRDSB Project No.: 34152-900
 Sample ID: 34152-900-AAM-AS1 Sample Date: 1-Sep-16
 Cassette Barcode No.: CU990730 Sample No.: 1856
 Project Location: Waterloo Oxford DSS Sampled By: MJM
 Analyst: MJM Analysis Date: 2-Sep-16
 Approved by: MJM Approval Date: 2-Sep-16

Date & Time On (m/d/yyyy hr:min)*:	9/1/2016 12:55	Sample Duration (hr:min):	3:00
Date & Time Off (m/d/yyyy hr:min)*:	9/1/2016 15:55	Sample Duration (min):	180
Sample Flow Rate (L/min):	15.00	Sample Volume (L):	2700

Total # of Fibres Counted =	33.5
Total # Fields Counted =	100
Fibres per Field	0.335
Fibres per Field (blank <7/100)	0
Diameter of Filter	25 mm
Effective Collection Area of Filter	385 mm ² (for 25 mm cassette)
Diameter of Field	0.1 mm
Field Area	0.00785 mm ²

Fibre Density = F (Fibre/mm²)

E = 0.335 Fibres per Field (sample) - 0 Fibres per Field (blank)
 Field Area 0.00785
 E = 42.68

Fibre Concentration = G Fibres/cubic centimetre (f/cc)

C = 42.68 x 385
 Sample Volume (L) 2700 x 1000 (conversion L to m³)
 C = 0.006 (f/cc) R.L. ≤ 0.007 (f/cc)

Notes:

- * Time displayed as 24 hour time.
- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS REPORT

Samples were analyzed using a Zeiss Axio Star Plus or Nikon Eclipse E100 Phase Contrast Microscope in accordance with NIOSH method 7400 "Asbestos and Other Fibres by PCM". The results of this report apply only to the materials tested.

CLIENT INFORMATION

Client Name: **WRDSB**

Project No: **34152-900**

Client Address: 51 Ardelt Avenue, Kitchener, Ontario

Site Address: 1206 Snyders Road W, Baden, Ontario


SAMPLING INFORMATION


Sampled by: MJM

Sampling date: 01-Sep-16

Analyzed by: MJM

Analysis date: 02-Sep-16

Analyst Signature: 

Manager's Signature: 

SAMPLE INFORMATION

Sample #: 1856

Cassette Barcode Number: CU990730

Sample ID: **34152-900-AAM-AS1**

Fibres/field: 0.335

Flow Rate (L/min): 15.00

Cassette Size (mm²): 385

Duration (min): 180

Field Size: 0.00785

Volume (L): 2700

R.L. ≤ **0.007** (f/cc)

Notes:

- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air

MTE Consultants Inc. participates and maintains proficient standing in the Canadian Association for Laboratory Accreditation Inc. (CALA) Asbestos Proficiency Testing for Asbestos and Other Fibres in air by Phase Contrast Microscopy (PCM) analysis under Membership Number 3827.

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS WORKSHEET

Client: WRDSB Project No.: 34152-900
 Sample ID: 34152-900-AAM-AS2 Sample Date: 1-Sep-16
 Cassette Barcode No.: CU990520 Sample No.: 1857
 Project Location: Waterloo Oxford DSS Sampled By: MJM
 Analyst: MJM Analysis Date: 2-Sep-16
 Approved by: MJM Approval Date: 2-Sep-16

Date & Time On (m/d/yyyy hr:min)*:	9/1/2016 12:58	Sample Duration (hr:min):	3:00
Date & Time Off (m/d/yyyy hr:min)*:	9/1/2016 15:58	Sample Duration (min):	180
Sample Flow Rate (L/min):	15.00	Sample Volume (L):	2700

Total # of Fibres Counted =	29.5
Total # Fields Counted =	100
Fibres per Field	0.295
Fibres per Field (blank <7/100)	0
Diameter of Filter	25 mm
Effective Collection Area of Filter	385 mm ² (for 25 mm cassette)
Diameter of Field	0.1 mm
Field Area	0.00785 mm ²

Fibre Density = F (Fibre/mm²)

E = Fibres per Field (sample) 0.295 - Fibres per Field (blank) 0
 E = 37.58 / Field Area 0.00785

Fibre Concentration = G Fibres/cubic centimetre (f/cc)

C = E 37.58 x Effective Collection Area 385
Sample Volume (L) 2700 x 1000 (conversion L to m³)
 C = 0.005 (f/cc) R.L. ≤ 0.007 (f/cc)

Notes:

- * Time displayed as 24 hour time.
- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS REPORT

Samples were analyzed using a Zeiss Axio Star Plus or Nikon Eclipse E100 Phase Contrast Microscope in accordance with NIOSH method 7400 "Asbestos and Other Fibres by PCM". The results of this report apply only to the materials tested.

CLIENT INFORMATION

Client Name: **WRDSB**

Project No: **34152-900**

Client Address: 51 Ardelt Avenue, Kitchener, Ontario

Site Address: 1206 Snyders Road W, Baden, Ontario

SAMPLING INFORMATION


Sampled by: MJM

Sampling date: 01-Sep-16

Analyzed by: MJM

Analysis date: 02-Sep-16

Analyst Signature: 

Manager's Signature: 

SAMPLE INFORMATION

Sample #: 1857

Cassette Barcode Number: CU990520

Sample ID: **34152-900-AAM-AS2**

Fibres/field: 0.295

Flow Rate (L/min): 15.00

Cassette Size (mm²): 385

Duration (min): 180

Field Size: 0.00785

Volume (L): 2700

R.L. ≤ **0.007** (f/cc)

Notes:

- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air

MTE Consultants Inc. participates and maintains proficient standing in the Canadian Association for Laboratory Accreditation Inc. (CALA) Asbestos Proficiency Testing for Asbestos and Other Fibres in air by Phase Contrast Microscopy (PCM) analysis under Membership Number 3827.

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS WORKSHEET

Client: WRDSB Project No.: 34152-900
 Sample ID: 34152-900-AAM-AS3 Sample Date: 1-Sep-16
 Cassette Barcode No.: CU990480 Sample No.: 1858
 Project Location: Waterloo Oxford DSS Sampled By: MJM
 Analyst: MJM Analysis Date: 2-Sep-16
 Approved by: MJM Approval Date: 2-Sep-16

Date & Time On (m/d/yyyy hr:min)*:	9/1/2016 12:58	Sample Duration (hr:min):	3:00
Date & Time Off (m/d/yyyy hr:min)*:	9/1/2016 15:58	Sample Duration (min):	180
Sample Flow Rate (L/min):	15.00	Sample Volume (L):	2700

Total # of Fibres Counted =	35.5
Total # Fields Counted =	100
Fibres per Field	0.355
Fibres per Field (blank <7/100)	0
Diameter of Filter	25 mm
Effective Collection Area of Filter	385 mm ² (for 25 mm cassette)
Diameter of Field	0.1 mm
Field Area	0.00785 mm ²

Fibre Density = F (Fibre/mm²)

E = Fibres per Field (sample) 0.355 - Fibres per Field (blank) 0
 E = 45.22 / Field Area 0.00785

Fibre Concentration = G Fibres/cubic centimetre (f/cc)

C = E 45.22 x Effective Collection Area 385
 C = 0.006 (f/cc) / Sample Volume (L) 2700 x 1000 (conversion L to m³)

R.L. ≤ 0.007 (f/cc)

Notes:

- * Time displayed as 24 hour time.
- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air

PHASE CONTRAST MICROSCOPY (PCM) ANALYSIS REPORT

Samples were analyzed using a Zeiss Axio Star Plus or Nikon Eclipse E100 Phase Contrast Microscope in accordance with NIOSH method 7400 "Asbestos and Other Fibres by PCM". The results of this report apply only to the materials tested.

CLIENT INFORMATION

Client Name: **WRDSB**

Project No: **34152-900**

Client Address: 51 Ardelt Avenue, Kitchener, Ontario

Site Address: 1206 Snyders Road W, Baden, Ontario


SAMPLING INFORMATION


Sampled by: MJM

Sampling date: 01-Sep-16

Analyzed by: MJM

Analysis date: 02-Sep-16

Analyst Signature: 

Manager's Signature: 

SAMPLE INFORMATION

Sample #: 1858

Cassette Barcode Number: CU990480

Sample ID: **34152-900-AAM-AS3**

Fibres/field: 0.355

Flow Rate (L/min): 15.00

Cassette Size (mm²): 385

Duration (min): 180

Field Size: 0.00785

Volume (L): 2700

R.L. ≤ **0.007** (f/cc)

Notes:

- R.L. = Reporting Limit based on Quantitation Limit for Sampling Volume based on approximately 40 fibres/100 fields
- (f/cc) = fibres per cubic centimetre of air

PROJECT INFORMATION

Inspection Date:	September 6, 2017	Project No.	100106.005
Report Issue Date:	September 7, 2017		
Project Name:	Asbestos Air Monitoring		
Site Address:	Waterloo-Oxford District Secondary School, 1206 Snyder's Road West, Baden, ON		
Client:	Waterloo Region District School Board (WRDSB)		
Client Supervisor:	Daniela Budure, Environmental Officer		
OnPoint Inspector:	Sean Hauck		
Arrival Time:	5:15 pm	Departure Time:	9:00 pm
		No. of Workers:	n/a

DISTRIBUTION

Issued to: Daniela Budure WRDSB daniela_budure@wrdsb.on.ca

WORK AREAS + DESCRIPTION OF WORK

Subject Areas OnPoint Environmental Solutions (OnPoint) was retained by the Waterloo Region District School Board (WRDSB) to perform proactive air testing to document the airborne fibre levels (including asbestos) within the following locations (hereafter referred to as the subject areas):

- Corridor adjacent Room 515
- Corridor adjacent Room 203
- Corridor adjacent Room 102
- **Air Monitoring – ACCEPTABLE**

FIELD OBSERVATIONS

Subject Areas	<p>Methodology</p> <ul style="list-style-type: none"> • OnPoint collected air samples for airborne fibre (including asbestos) analysis using 25mm Mixed Cellulose Ester (MCE) cassettes with 0.8 micrometer (µm) pore size and Allegro high volume sample pumps calibrated to a flow rate of approximately 15 litres per minute (L/min). • All samples were analysed following the Phase Contrast Microscopy (PCM) method as specified in the NIOSH 7400 method. The PCM method does not allow discrimination between asbestos and non-asbestos fibres. All fibres that meet the counting criteria are included in the count. Using the fibre count data and the sampling volume, an estimate of the average airborne fibre concentration during the sampling period was made.
----------------------	---

Results

- All air samples reported concentrations of total fibres to be less than 0.01 fibres per cubic centimetre (f/cc) of air. Ontario Regulation 490/09 Designated Substances prescribes an acceptable Time Weighted Average Exposure Value (TWAEV) for asbestos fibre of not more than 0.1 f/cc. The reported concentrations (<0.01 f/cc) indicate that airborne fibre (including asbestos) levels within the subject areas are well below the criterion noted above. One field blank was collected for quality control purposes. Analysis of the field blank showed 0 fibres per 100 fields counted.
- Photographs of the air monitoring equipment are provided below.

AIR MONITORING RESULTS – Phase Contrast Microscopy (PCM)*

Type	Sample No.	Sampling Location	Start Time	Stop Time	Flow Rate (L/min)	Duration (Minutes)	Air Volume (L)	Result (f/cc of air)
OC	CZ370501	Corridor adjacent Room 515	5:30 pm	8:30 pm	15	180	2,700	< 0.01
OC	CZ370429	Corridor adjacent Room 203	5:40 pm	8:35 pm	15	175	2,625	< 0.01
OC	CZ370414	Corridor adjacent Room 102	5:45 pm	8:40 pm	15	175	2,625	< 0.01
QC	CZ370379	Field Blank	N/A	N/A	N/A	N/A	N/A	0 fibres/100 fields

Notes:

OCCUPIED (OC)
QUALITY CONTROL (QC)

Area samples were collected in regularly occupied spaces (i.e., not within an asbestos abatement work area).

Field blank samples were collected in a manner representing the actual handling of associated samples in a sample set for quality control purposes.

f/cc fibres per cubic centimeter of air
L/min litres/minute

* Air monitoring and analysis was performed following the NIOSH 7400 method using Phase Contrast Microscopy (PCM)

CONCLUSION

PCM analysis of the collected air samples confirmed airborne fibre concentrations (including asbestos) were within the acceptable range (i.e., below 0.1 fibres/cc of air). As such, the subject areas are acceptable for continued occupancy.

[https://onpointes-my.sharepoint.com/personal/aandriotis_onpointenvironmental_com/documents/onpoint es/projects/100106 wrdsb/005 rfpacmairstestvarious/sites/waterloo oxford/inspection rpt/100106.005 air sampling waterloo-oxford s.s. baden on wrdsb sept 7 2017.docx](https://onpointes-my.sharepoint.com/personal/aandriotis_onpointenvironmental_com/documents/onpoint%20es/projects/100106%20wrdsb/005%20rfpacmairstestvarious/sites/waterloo%20oxford/inspection%20rpt/100106.005%20air%20sampling%20waterloo-oxford%20s.s.%20baden%20on%20wrdsb%20sept%207%202017.docx)

PHOTOGRAPHS



Photo 1: Air monitoring equipment
Corridor adjacent Room 515.



Photo 2: Air monitoring equipment
Corridor adjacent Room 203.



Photo 3: Air monitoring equipment
Corridor adjacent Room 102.

PROJECT INFORMATION

Inspection Date:	August 21, 2019	Project No.	100106.029
Project Name:	Occupied Air Monitoring for Asbestos Fibres		
Site Address:	Waterloo-Oxford District Secondary School, 1206 Snyder's Road West, Baden, ON		
Client:	Waterloo Region District School Board (WRDSB)		
Client Supervisor:	Daniela Budure, Environmental Officer		
OnPoint Inspector:	David Niemand		
Arrival Time:	2:50 pm	Departure Time:	6:10 pm
		No. of Workers:	n/a

DISTRIBUTION

Issued to:	Daniela Budure	WRDSB	daniela_budure@wrdsb.on.ca
-------------------	----------------	-------	----------------------------

WORK AREAS + DESCRIPTION OF WORK

Subject Areas OnPoint Environmental Solutions Inc. (OnPoint) was retained by the Waterloo Region District School Board (WRDSB) to perform proactive air testing to document the airborne fibre levels (including asbestos) within the following locations (hereafter referred to as the subject areas):

- Corridor (adjacent Room 508)
- Corridor (adjacent Room 203)
- Corridor (adjacent Room 102)

The air monitoring was requested as part of an ongoing program to assess airborne asbestos fibre concentrations in occupied areas of the school in conjunction with ongoing asbestos management.

- **Air Monitoring – ACCEPTABLE**

FIELD OBSERVATIONS

Subject Areas	Methodology
	<ul style="list-style-type: none"> • OnPoint collected air samples for airborne fibre (including asbestos) analysis using 25mm Mixed Cellulose Ester (MCE) cassettes with 0.8 micrometer (µm) pore size and Allegro high-volume sample pumps calibrated to a flow rate of approximately 15 litres per minute (L/min). • All samples were analysed following the Phase Contrast Microscopy (PCM) method as specified in the NIOSH 7400 method. The PCM method does not allow discrimination between asbestos and non-asbestos fibres. All fibres that meet the counting criteria are included in the count. Using the fibre count data and the sampling volume, an estimate of the average airborne fibre concentration during the sampling period was made.

Results

- All air samples reported concentrations of total fibres to be less than 0.01 fibres per cubic centimetre (f/cc) of air. Ontario Regulation 490/09 Designated Substances prescribes an acceptable Time Weighted Average Exposure Value (TWAEV) for asbestos fibre of not more than 0.1 f/cc. The reported concentrations (<0.01 f/cc) indicate that airborne fibre (including asbestos) levels within the subject areas are well below the criterion noted above. One field blank was collected for quality control purposes. Analysis of the field blank showed 0 fibres per 100 fields counted.
- Photographs of the air monitoring equipment are provided below.

AIR MONITORING RESULTS – Phase Contrast Microscopy (PCM)*

Type	Sample No.	Sampling Location	Start Time	Stop Time	Flow Rate (L/min)	Duration (Minutes)	Air Volume (L)	Result (f/cc of air)
OC	CN659715	Corridor (adjacent Class 508)	2:53 pm	5:52 pm	15	179	2,685	< 0.01
OC	CN659724	Corridor (adjacent Class 203)	2:58 pm	5:58 pm	15	180	2,700	< 0.01
OC	CN659727	Corridor (adjacent Class 102)	3:04 pm	6:02 pm	15	178	2,670	< 0.01
QC	CN659714	Field Blank	N/A	N/A	N/A	N/A	N/A	0 fibres/100 fields

Notes:

- OCCUPIED (OC)** Area samples were collected in regularly occupied spaces (i.e., not within an asbestos abatement work area).
- QUALITY CONTROL (QC)** Field blank samples were collected in a manner representing the actual handling of associated samples in a sample set for quality control purposes.
- f/cc** fibres per cubic centimeter of air
- L/min** litres/minute
- *** Air monitoring and analysis was performed following the NIOSH 7400 method using Phase Contrast Microscopy (PCM)

CONCLUSION

PCM analysis of the collected air samples confirmed airborne fibre concentrations (including asbestos) were within the acceptable range (i.e., below 0.1 fibres/cc of air). As such, the subject areas are acceptable for continued occupancy.

[https://onpointes-my.sharepoint.com/personal/aandriotis_onpointenvironmental_com/documents/onpoint es/projects/100100/100106 wrdsb/029 acmairstestvarious/sites/waterloo oxford/inspection rpt/100106.029 air sampling waterloo-oxford ss baden on wrdsb aug 21 2019.docx](https://onpointes-my.sharepoint.com/personal/aandriotis_onpointenvironmental_com/documents/onpoint%20es/projects/100100/100106%20wrdsb/029%20acmairstestvarious/sites/waterloo%20oxford/inspection%20rpt/100106.029%20air%20sampling%20waterloo-oxford%20ss%20baden%20on%20wrdsb%20aug%2021%202019.docx)

PHOTOGRAPHS



Photo 1: Air monitoring equipment - Corridor (adjacent Room 508).



Photo 2: Air monitoring equipment - Corridor (adjacent Room 203).



Photo 3: Air monitoring equipment - Corridor (adjacent Room 102).



MTE Consultants

520 Bingham Centre Drive, Kitchener, Ontario N2B 3X9

April 27, 2022

MTE File No.: C34532-936

Waterloo Region District School Board
51 Ardelt Avenue
Kitchener, ON N2C 2R5

**RE: Results of Total Airborne Fibre Sampling at
Waterloo Oxford District Secondary School
1206 Snyder's Road West, Baden, Ontario**

MTE Consultants Inc. (MTE) was retained by the Waterloo Region District School Board (WRDSB) to complete a sampling program for airborne fibres in conjunction with ongoing asbestos management at Waterloo Oxford District Secondary School (WODSS) located at 1206 Snyder's Road West in Baden, Ontario.

Background

In September 2012, inspection services, documentation, and air monitoring programs were developed and conducted by MTE. A portion of the above mentioned monitoring program included ongoing sampling for total airborne fibre analysis by Phase Contrast Microscopy (PCM) to assess any potential risk of building occupant exposure to airborne asbestos fibres. Air sampling will continue as part of the ongoing monitoring program, and sampling will be conducted on a bi-annual basis, as requested by the WRDSB.

As part of the ongoing monitoring program air sampling was conducted between September, 2012, March 2013 and August 2016. Analytical results from the previous sampling events are documented in MTE's previous reports.

This report should be read in conjunction with previous reports related to airborne fibre sampling at the school.

Sampling is conducted on an annual basis, as requested by the WRDSB.

Scope of Work

The scope of MTE's services for this assignment was:

- Collection of three (3) air samples from selected locations on the First and Second Floors in accordance with the National Institute for Occupational Safety and Health (NIOSH) Method 7400;
- Submission of samples to an accredited and/or qualified laboratory for PCM Analysis;
- Interpretation of analytical results with respect to occupational worker exposure; and
- Preparation of a letter report of findings with appropriate recommendations, if required.

Methodology

In conjunction with the ongoing management program, air samples were collected by MTE from selected locations on April 5, 2022. A total of three (3) air samples were collected. Samples were collected in accordance with The National Institute for Occupational Safety and Health (NIOSH) Method 7400 and were analyzed by Paracel Laboratories Inc. Paracel participates and maintains proficient standing in the Canadian Association for Laboratory Accreditation (CALA) proficiency testing in asbestos and other fibres in air by Phase Contrast Microscopy Analysis under Membership number 3762. Table 1 provides a summary of sample locations and laboratory analytical results.

Table 1: Summary of Airborne Fibre Concentrations at Selected Sample Locations throughout WODSS on April 4, 2022 As Determined By Phase Contrast Microscopy

Sample Name	Sample Location	Sample Air Volume Collected (L)	Analytical Results: Fibres per cubic centimetre of Air (f/cc)
AC1-WODSS	Corridor 801 @ Room 103	2,400	0.002
AC2-WODSS	Room 123	2,400	<0.001
AC3-WODSS	Corridor 810 @ Room 507	2,400	<0.001

Discussion

Airborne Fibres

All three air samples collected reported concentrations of total airborne fibres to be below 0.01 fibres per cubic centimetre of air (f/cc). Two of the three samples reported below the laboratory detection limit of 0.001 f/cc.

It should be noted that the analysis method does not distinguish between asbestos fibres and other fibre sources. Sample method detection limits have been rounded to the nearest significant digit. Ontario Regulation 490/09 Designated Substances prescribes an acceptable Time Weighted Average Exposure Value (TWAEV) to asbestos fibre of not more than 0.1 fibres per cubic centimetre of air (f/cc). Standard industrial hygiene practice considers a concentration greater than one half the TWAEV (0.05 f/cc) as actionable in order to control exposure and ensure worker safety. Ontario Regulation 278/05 Designated Substance – Asbestos on Construction Projects and in Buildings and Repair Operations prescribes an acceptable post asbestos removal air clearance concentration of not more than 0.01 f/cc or one tenth the TWAEV. This concentration is deemed protective of human health for workers and occupants of the building. All samples reported concentrations of total airborne fibres to be below the clearance criteria of 0.01 f/cc. The reported concentrations do not suggest an overexposure to airborne asbestos for workers or building occupants.

It should be noted that asbestos-containing spray-applied fireproofing still exists within the building. The results of the current and historical air sampling do not imply a risk-free facility and all work which may disturb spray-applied fireproofing, other asbestos-containing materials and potentially asbestos-contaminated infrastructure, must be conducted in compliance with Ontario Regulation 278/05.

Conclusions and Recommendations

Based on analytical results the following conclusions are presented:

- Total airborne fibre concentrations within the sampled locations are well below the Ontario Ministry of Labour TWAEV acceptable abatement and clearance criteria prescribed in Ontario Regulation 490/09 and 278/05 respectively.
- The reported concentrations in the air samples do not suggest workers or building occupants are at any elevated risk of over exposure to airborne asbestos fibres, under current site conditions.
- These findings should be incorporated into the building asbestos audit and Asbestos Management Program.
- If work is required which will disturb or is likely to disturb asbestos-containing material, the work must be conducted in accordance with Ontario Regulation 278/05 by trained and certified asbestos removal contractors.

For Tender Purposes

Limitation

Services performed by **MTE Consultants Inc.** (MTE) were conducted in a manner consistent with the level of care and skill ordinarily exercised by members of the Environmental Engineering & Consulting profession. No other representation expressed or implied as to the accuracy of the information, conclusions or recommendations is included or intended in this report.

This report was completed for the sole use of MTE and Waterloo Region District School Board. It was completed in accordance with the Scope of Work. As such, this report may not deal with all issues potentially applicable to the site and may omit issues, which are or may be of interest to the reader. MTE makes no representation that the present report has dealt with all important environmental features, except as provided in the Scope of Work. All findings and conclusions presented in this report are based on site conditions, as they existed during the time period of the investigation. This report is not intended to be exhaustive in scope or to imply a risk-free facility.

Some areas could not be investigated due to non-destructive, non-invasive, inspection restrictions or prohibited access. Although the presence of asbestos-containing materials (ACM) has been anticipated in these areas where reasonable, the accuracy of such information must be confirmed before any potential disturbance of materials which may contain asbestos. It is also possible that ACM may be visually or physically concealed by but not necessarily limited to ceilings, walls, bulkheads, floors, roof systems or other similar features or structures.

Any use which a third party makes of this report, or any reliance on, or decisions to be made based upon it, are the responsibility of such third parties. MTE accepts no responsibility for liabilities incurred by or damages, if any, suffered by any third party as a result of decisions made or actions taken, based upon this report. Others with interest in the site should undertake their own investigations and studies to determine how or if the condition affects them or their plans.

It should be recognized that the passage of time may affect the views, conclusions and recommendations (if any) provided in this report because environmental conditions of a property can change. Should additional or new information become available, MTE recommends that it be brought to our attention in order that we may re-assess the contents of this report.

Yours truly,

MTE Consultants Inc.



Jason Scozzafava, B.Sc., C.Tech.

Senior Technologist, Indoor Environments
519-743-6500 ext. 1354

jscozzafava@mte85.com



Martin Mielke, B.Sc., CRSP

Technical Practice Leader, Indoor Environments
519-743-6500 ext. 1318

mmielke@mte85.com

JAS: apm

Attach

M:\34532\936\WODSS\34532-936_2022-04-27_RptAirSampling_WODSS.docx

Certificate of Analysis

MTE Consultants Inc. (Kitchener)

520 Bingemans Centre Dr.
Kitchener, ON N2B 3X9
Attn: Paul Semeniuk

Client PO: 34532-936

Project: 34532-936 WODSS

Custody:

Report Date: 12-Apr-2022

Order Date: 7-Apr-2022

Order #: 2215474

This Certificate of Analysis contains analytical data applicable to the following samples as submitted:

Parcel ID

2215474-01

2215474-02

2215474-03

Client ID

AC1-WODSS - Cor 801

AC2-WODSS - Rm 123

AC3-WODSS - Cor 810

Approved By:



Emma Diaz

Senior Analyst

Certificate of Analysis
Client: MTE Consultants Inc. (Kitchener)

Client PO: 34532-936

Report Date: 12-Apr-2022

Order Date: 7-Apr-2022

Project Description: 34532-936 WODSS

Asbestos - Air PCM Fiber Count

Parcel ID	Sample Date	Air Volume(L)	Fields Read	Fibers Detected	Fibers/mm2	LOD (f/cc)	Fibers/cc	Sample Notes
Client ID: AC1-WODSS - Cor 801								
2215474-01	04-Apr-22	2400	100	10.0	12.74	0.001	0.002	
Client ID: AC2-WODSS - Rm 123								
2215474-02	04-Apr-22	2400	100	4.0	5.1	0.001	<0.001	
Client ID: AC3-WODSS - Cor 810								
2215474-03	04-Apr-22	2400	100	1.0	1.27	0.001	<0.001	

* Sample results for fiber density (Fibers/mm2) and concentration (Fibers/cc) have been corrected for field blank data if available.

Analysis Summary Table

Analysis	Method Reference/Description	Lab Location	Analysis Date
Asbestos and Other Fibers by PCM	NIOSH 7400 - Asbestos and Other Fibers by PCM	1 - Mississauga	12-Apr-22

Mississauga Lab: 15 - 6800 Kitimat Rd Mississauga, Ontario, L5N 5M1

Work Order Revisions | Comments

None

NOTE: Sample volume was provided by the client and has been used in the calculations. This can affect the validity of the final result.

2215474



Office
319 St. Laurent Blvd.
8, Ontario K1G 4J8
416-749-1947
racel@paracellabs.com

Chain of Custody
(Lab Use Only)

Page ___ of ___

Turnaround Time:

- ☐ Immediate ☐ 1 Day
☐ 4 Hour ☐ 2 Day
☐ 8 Hour ☐ 3 Day
☒ Regular

Date Required: _____

Client Name: MTE Consultants Inc.
Contact Name: Paul Semeniuk
Address: 520 Bingmans Centre Drive
Kitchener ON N2B 3X9
Telephone: 519-743-6500
Project Reference: WODSS
Quote #: 22-084 MTE Standing Offer
PO #: 34532-936
Email Address: jscozzafava@mte85.com
psemeniuk@mte85.com

ASBESTOS & MOLD ANALYSIS

Matrix: ☒ Air ☐ Bulk ☐ Tape Lift ☐ Swab ☐ Other
Regulatory Guideline: ☒ ON ☐ QC ☐ AB ☐ SK ☐ Other:
Analyses: ☐ Microscopic Mold ☐ Culturable Mold ☐ Bacteria GRAM ☒ PCM Asbestos ☐ PLM Asbestos ☐ Chatfield Asbestos ☐ TEM Asbestos

Parcel Order Number:

2215474

Asbestos - Bulk

Sample ID	Sampling Date	Air Volume (L)	Analysis Required	Identify Distinct Building Materials to Be Analyzed (if not specified, all materials identified will be analyzed) *	Positive Stop?
1 AC1-WODSS-Cor 801	4/4/2022	2400	PCM		<input type="checkbox"/>
2 AC2-WODSS-Rm 123	4/4/2022	2400	PCM		<input type="checkbox"/>
3 AC3-WODSS-Cor 810	4/4/2022	2400	PCM		<input type="checkbox"/>
4					<input type="checkbox"/>
5					<input type="checkbox"/>
6					<input type="checkbox"/>
7					<input type="checkbox"/>
8					<input type="checkbox"/>
9					<input type="checkbox"/>
10					<input type="checkbox"/>
11					<input type="checkbox"/>
12					<input type="checkbox"/>

* If left blank, all distinct materials identified in the samples will be analyzed and reported separately as per EPA 600/R-93/116. Additional charges will apply.

Comments:

Relinquished By (Sign):	Received at Depot:	Received at Lab:	Method of Delivery:
Relinquished By (Print): Jason Scozzafava		Verified By:	
Date/Time: April 6, 2022	Date/Time:	Date/Time: Apr 7/22	Date/Time: Apr 7/22

12.47

13.44

Client Name: MTE Consultants Inc.	Project Reference: WODSS	Turnaround Time: <input type="checkbox"/> Immediate <input type="checkbox"/> 1 Day <input type="checkbox"/> 4 Hour <input type="checkbox"/> 2 Day <input type="checkbox"/> 8 Hour <input type="checkbox"/> 3 Day <input checked="" type="checkbox"/> Regular
Contact Name: Paul Semeniuk	Quote #: 22-084 MTE Standing Offer	
Address: 520 Bingmans Centre Drive Kitchener ON N2B 3X9	PO #: 34532-936	
Telephone: 519-743-6500	Email Address: jscozzafava@@mte85.com psemeniuk@mte85.com	
Date Required: _____		

ASBESTOS & MOLD ANALYSIS

Matrix: ☒ Air ☐ Bulk ☐ Tape Lift ☐ Swab ☐ Other **Regulatory Guideline:** ☒ ON ☐ QC ☐ AB ☐ SK ☐ Other:

Analyses: ☐ Microscopic Mold ☐ Culturable Mold ☐ Bacteria GRAM ☒ PCM Asbestos ☐ PLM Asbestos ☐ Chatfield Asbestos ☐ TEM Asbestos

Paracel Order Number:

				Asbestos - Bulk	
Sample ID				Identify Distinct Building Materials to Be Analyzed (if not specified, all materials identified will be analyzed) *	Positive Stop?
1	AC1-WODSS-Cor 801	4/4/2022	2400	PCM	<input type="checkbox"/>
2	AC2-WODSS-Rm 123	4/4/2022	2400	PCM	<input type="checkbox"/>
3	AC3-WODSS-Cor 810	4/4/2022	2400	PCM	<input type="checkbox"/>
4					<input type="checkbox"/>
5					<input type="checkbox"/>
6					<input type="checkbox"/>
7					<input type="checkbox"/>
8					<input type="checkbox"/>
9					<input type="checkbox"/>
10					<input type="checkbox"/>
11					<input type="checkbox"/>
12					<input type="checkbox"/>

* If left blank, all distinct materials identified in the samples will be analyzed and reported separately as per EPA 600/R-93/116. Additional charges will apply.

Comments:			Method of Delivery:
Relinquished By (Sign):	Received at Depot:	Received at Lab:	Verified By:
Relinquished By (Print): Jason Scozzafava	Date/Time: April 6, 2022	Date/Time:	Date/Time:



1-220 Spring Valley Rd.

Kitchener, ON N2H 5X8

Waterloo Region (519) 578-0200 Toronto (416) 283-2673

office@ddkductcleaning.com

Certificate of Completion

This is to verify that work has been completed at:

Waterloo Oxford District Secondary School

1206 Snyder Rd. W., Baden

Work completed on: November 29th & 30th, 2022

Description:

Cleaned ground floor return/exhaust air ductwork, grilles and diffusers serving the "100" wing classrooms/teachers rooms and back to the drops from the AHU above.



The HVAC Inspection, Maintenance
and Restoration Association



1-220 Spring Valley Rd.

Kitchener, ON N2H 5X8

Waterloo Region (519) 578-0200 Toronto (416) 283-2673

office@ddkductcleaning.com

Certificate of Completion

This is to verify that work has been completed at:

Waterloo Oxford District Secondary School

1206 Snyder Rd. W., Baden

Work completed on: January 3-5, 2023

Description:

Cleaned second floor return/exhaust air ductwork, grilles and diffusers serving the "100" wing classrooms rooms and back to the AHU in the mechanical room.



The HVAC Inspection, Maintenance
and Restoration Association